

Technical Data Sheet

IPETHENE® 2050

Low Density Polyethylene



Product Description

IPETHENE® 2050 is a low-density polyethylene, produced by high-pressure autoclave technology.

Features:

- No additives
- Ultra-High flow
- Good Processability
- Low warpage

Uses:

- Carpet Backing
- Baskets
- Hot-melt adhesives
- Thin walled articles
- High filler compounds

Processing Methods:

- Compounding coating
- Injection molding

Properties	Method	Typical Value*	Unit
Physical			
Melt Flow Rate	(190°C/2.16 kg) ISO 1133	200	g/10 min
Density	ISO 1183-A	0.915	g/cm ³
Shore Hardness	'D' Scale ISO 868	39	
Thermal			
Peak Melting Temperature	By DSC ISO 11357-3	105	°C
Vicat Softening Temperature	(10 N) ISO 306	75	°C
Mechanical			
Tensile Stress at Break	ISO 527-2	7.0	MPa
Tensile Strain at Break	ISO 527-2	110	%

*Typical values; not to be construed as specifications.

Processing Recommendations

IPETHENE® 2050 can be easily processed on conventional injection molding machines. Due to differences in machine type, part shape and mold design, processing conditions should be optimized for each production line.

Typical temperature profile: Barrel 150-200°C; Mold 10-40°C.

Health, Quality, Regulations and Safety

This product is not classified as dangerous substance and intended for industrial use, to produce plastic articles. Material safety data sheets, international standards certificates and other regulatory documents are available on our website. Carmel Olefins products have not been tested and therefore not validated for use in pharmaceutical/medical applications, and their suitability for these uses cannot be guaranteed. It is the customer's responsibility to test and approve their technical and regulatory suitability in order to satisfy themselves as to the particular purpose and application(s).

Carmel Olefins Ltd. POB 1468 Haifa 31014 Israel
Website: <http://www.Carmel-Olefins.co.il>
Email: techserv@caol.co.il

Date: April 2026

The information contained herein is to our knowledge accurate and reliable as of the date of publication. Carmel Olefins recommends its customers to review both the manufacturing processes and applications of Carmel Olefins products to ensure, that the products are not used for purposes they are not intended or tested for. Carmel Olefins extends no warranties and makes no representations as to the accuracy or completeness of the information contained herein and assumes no responsibility regarding the consequences of its use or for any printing errors. Our products are intended for sale to industrial and commercial customers. Data in this document relates only to the specific product and may not be valid for any combination of this product with other materials. It is the customer's responsibility to inspect and test our products in order to satisfy himself as to the suitability of the products for the customer's particular purpose. The customer is responsible for its employees' safety and the appropriate, safe and legal use, processing, handling and disposing of our products and packaging. Carmel Olefins shall not be liable for any consequential, incidental or indirect damages resulting from this statement or its use.

