



Technical Data Sheet

DOW™ LDPE 640I Low Density Polyethylene Resin

Description

Dow™ LDPE 640I Low Density Polyethylene Resin is a general-purpose liner resin for thin gauge applications requiring good drawdown and excellent toughness.

Main Characteristics

- Low density polyethylene (LDPE)
- A barefoot general purpose general liner resin
- For blown and cast film extrusion
- Optimum gauge range: 0.8-3.0 mil

Complies with

- U.S. FDA 21 CFR 177.1520 (c) 2.2.
- U.S. FDA -DMF
- EU, No 10/2011
- Canadian HPFB No Objection (With Limitations)
- U.S. Pharmacopoeia (USP) - Class VI

Consult the regulations for complete details.

Additive

- Antiblock: No
- Slip: No
- Processing aid: No

Typical Properties¹

Physical	Nominal Value	Unit (English)	Nominal Value	Unit (SI)	Test Method ²
Density	0.920	g/cm ³	0.920	g/cm ³	ASTM D792
Base Density ³	0.920	g/cm ³	0.920	g/cm ³	Internal Method
Melt Index (190°C/2.16 kg)	2.0	g/10 min	2.0	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (ESCR)	2.00	hr	2.00	hr	ASTM D1693
Mechanical	Nominal Value	Unit (English)	Nominal Value	Unit (SI)	Test Method
Tensile Strength ⁴					ASTM D638
Yield	1300	psi	8.96	MPa	
Break	1600	psi	11.0	MPa	

1. Typical properties: these are not to be construed as specifications. Users should confirm results by their own tests.
2. ASTM: American Society for Testing and Materials
3. Base density is estimated using the assumption that every 1000 ppm of antiblock in the finished product raises the density of the polymer by 0.0006 g/cm³. Base density is the estimated density of the polymer if it did not contain any antiblock.
4. Plaque molded and tested in accordance with ASTM D4976.



Typical Properties (Cont.)

Mechanical	Nominal Value	Unit (English)	Nominal Value	Unit (SI)	Test Method
Tensile Elongation ⁴					ASTM D638
Yield	4.0	%	4.0	%	
Break	600	%	600	%	
Flexural Modulus — 2% Secant ⁴	34000	psi	234	MPa	ASTM D790
Films	Nominal Value	Unit (English)	Nominal Value	Unit (SI)	Test Method
Film Puncture Resistance					Internal Method
1.0 mil (25 µm), Cast Film	45.0	ft-lb/in ³	3.72	J/cm ³	
2.0 mil (51 µm), Blown Film	35.0	ft-lb/in ³	2.90	J/cm ³	
Film Toughness					ASTM D882
MD: 1.0 mil (25 µm), Cast Film	1790	ft-lb/in ³	148	J/cm ³	
MD: 2.0 mil (51 µm), Blown Film	1920	ft-lb/in ³	159	J/cm ³	
TD: 1.0 mil (25 µm), Cast Film	2310	ft-lb/in ³	191	J/cm ³	
TD: 2.0 mil (51 µm), Blown Film	2230	ft-lb/in ³	184	J/cm ³	
Secant Modulus					ASTM D882
2% Secant, MD: 2.0 mil (51 µm), Blown Film	26200	psi	181	MPa	
2% Secant, TD: 2.0 mil (51 µm), Blown Film	30000	psi	207	MPa	
Tensile Strength					ASTM D882
MD: Yield, 1.0 mil (25 µm), Cast Film	1850	psi	12.7	MPa	
MD: Yield, 2.0 mil (51 µm), Blown Film	1790	psi	12.3	MPa	
TD: Yield, 1.0 mil (25 µm), Cast Film	1460	psi	10.0	MPa	
TD: Yield, 2.0 mil (51 µm), Blown Film	1760	psi	12.1	MPa	
MD: Break, 1.0 mil (25 µm), Cast Film	4970	psi	34.3	MPa	
MD: Break, 2.0 mil (51 µm), Blown Film	3600	psi	24.8	MPa	
TD: Break, 1.0 mil (25 µm), Cast Film	3240	psi	22.3	MPa	
TD: Break, 2.0 mil (51 µm), Blown Film	3330	psi	23.0	MPa	
Tensile Elongation					ASTM D882
MD: Break, 1.0 mil (25 µm), Cast Film	260	%	260	%	
MD: Break, 2.0 mil (51 µm), Blown Film	420	%	420	%	
TD: Break, 1.0 mil (25 µm), Cast Film	700	%	700	%	
TD: Break, 2.0 mil (51 µm), Blown Film	670	%	670	%	
Dart Drop Impact					ASTM D1709A
1.0 mil (25 µm), Cast Film	45	g	45	g	
2.0 mil (51 µm), Blown Film	150	g	150	g	
Elmendorf Tear Strength					ASTM D1922
MD: 1.0 mil (25 µm), Cast Film	190	g	190	g	
MD: 2.0 mil (51 µm), Blown Film	500	g	500	g	
TD: 1.0 mil (25 µm), Cast Film	130	g	130	g	
TD: 2.0 mil (51 µm), Blown Film	280	g	280	g	



Typical Properties (Cont.)

Impact	Nominal Value	Unit (English)	Nominal Value	Unit (SI)	Test Method
Tensile Impact Strength ^{4,5}	70.0	ft-lb/in ³	147	kJ/m ²	ASTM D1822
Hardness	Nominal Value	Unit (English)	Nominal Value	Unit (SI)	Test Method
Durometer Hardness ⁴ (Shore D)	45		45		ASTM D2240
Thermal	Nominal Value	Unit (English)	Nominal Value	Unit (SI)	Test Method
Deflection Temperature Under Load ³ 66 psi (0.45 MPa), Unannealed	101	°F	38.3	°C	ASTM D648
Brittleness Temperature	< -105	°F	< -76.1	°C	ASTM D746
Vicat Softening Temperature	203	°F	95.0	°C	ASTM D1525
Melting Temperature (DSC)	233	°F	112	°C	Internal Method
Peak Crystallization Temperature (DSC)	209	°F	98.3	°C	Internal Method
Optical	Nominal Value	Unit (English)	Nominal Value	Unit (SI)	Test Method
Gloss					ASTM D2457
45°, 2.0 mil (50.8 µm), Blown Film	66		66		
45°, 1.0 mil (25.4 µm), Cast Film	75		75		
Haze					ASTM D1003
2.0 mil (50.8 µm), Blown Film	7.60	%	7.60	%	
1.0 mil (25.4 µm), Cast Film	4.80	%	4.80	%	

Extrusion Notes

Fabrication Conditions For Cast Film:

- Screw A, Size: 2 in. (51 mm); 30:1 L/D
 - Melt Temperature: 501°F (261°C)
 - Screw Speed: 32 rpm
- Screw B, Size: 2.5 in. (63.5 mm); 30:1 L/D
 - Melt Temperature: 501°F (261°C)
 - Screw Speed: 32 rpm
- Screw C, Size: 2.5 in. (63.5 mm); 30:1 L/D
 - Melt Temperature: 501°F (261°C)
 - Screw Speed: 32 rpm
- Screw D, Size: 2.5 in. (63.5 mm); 30:1 L/D
 - Melt Temperature: 501°F (261°C)
 - Screw Speed: 32 rpm
- Screw E, Size: 2 in. (51 mm); 30:1 L/D
 - Melt Temperature: 501°F (261°C)
 - Screw Speed: 32 rpm
- Screw Type: DSB II
- Chill Roll Temperature: 70°F (21°C)
- Line Speed: 400 fpm (123 m/min)

5. Type S.



Typical Properties (Cont.)

Extrusion Notes

Fabrication Conditions for Blown Film:

- Screw Size: 2.5 in. (63.5 mm) 30:1 L/D
- Screw Type: Single Flight Double Mix
- Die Gap: 40 mil (1.02 mm)
- Melt Temperature: 390°F (199°C)
- Output: 7 lb/hr/in. of die circumference
- Die Diameter: 6 in.
- Blow-up Ratio: 2.5:1
- Screw Speed: 60 rpm
- Frost Line Height: 25 in. (635 mm)

Product Stewardship

Dow has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our product stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with Dow products — from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

Customer Notice

Dow strongly encourages its customers to review both their manufacturing processes and their applications of Dow products from the standpoint of human health and environmental quality to ensure that Dow products are not used in ways for which they are not intended or tested. Dow personnel are available to answer your questions and to provide reasonable technical support. Dow product literature, including safety data sheets, should be consulted prior to use of Dow products. Current safety data sheets are available from Dow.

Medical Applications Policy

NOTICE REGARDING MEDICAL APPLICATION RESTRICTIONS: Dow will not knowingly sell or sample any product or service ("Product") into any commercial or developmental application that is intended for:

- long-term or permanent contact with internal bodily fluids or tissues. "Long-term" is contact which exceeds 29 calendar days;
- use in cardiac prosthetic devices regardless of the length of time involved ("cardiac prosthetic devices" include, but are not limited to, pacemaker leads and devices, artificial hearts, heart valves, intra-aortic balloons and control systems, and ventricular bypass-assisted devices);
- use as a critical component in medical devices that support or sustain human life;
- use specifically by pregnant women or in applications designed specifically to promote or interfere with human reproduction; or
- use as an ingredient of a pharmaceutical injectable application.

Dow requests that customers considering use of Dow products in medical applications notify Dow so that appropriate assessments may be conducted. Dow does not endorse or claim suitability of its products for specific medical applications. It is the responsibility of the medical device or pharmaceutical manufacturer to determine that the Dow product is safe, lawful, and technically suitable for the intended use. **DOW MAKES NO WARRANTIES, EXPRESS OR IMPLIED, CONCERNING THE SUITABILITY OF ANY DOW PRODUCT FOR USE IN MEDICAL APPLICATIONS.**



Contact:
www.dow.com/contact

NOTICE: No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, the Customer is responsible for determining whether products and the information in this document are appropriate for the Customer's use and for ensuring that the Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Dow assumes no obligation or liability for the information in this document. **NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.**

NOTICE: If products are described as "experimental" or "developmental": (1) product specifications may not be fully determined; (2) analysis of hazards and caution in handling and use are required; (3) there is greater potential for Dow to change specifications and/or discontinue production; and (4) although Dow may from time to time provide samples of such products, Dow is not obligated to supply or otherwise commercialize such products for any use or application whatsoever.

NOTICE: This data is based on information Dow believes to be reliable, as demonstrated in controlled laboratory testing. They are offered in good faith, but without guarantee, as conditions and method of use of Dow products are beyond Dow's control. Dow recommends that the prospective user determine the suitability of these materials and suggestions before adopting them on a commercial scale.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability for the accuracy and completeness of such information.

For additional information, not covered by the content of this document, contact us via our website
http://www.dow.com/products_services/.

This document is intended for use within Asia Pacific, Europe, and North America.

PETROMALL

