



Formosa Plastics®

Formolene® PP

## Formolene® 6520A

### Impact Copolymer for Injection Molding

Formolene® 6520A is a medium impact copolymer of polypropylene characterized by its easy mold flow, physical property balance and excellent dimensional stability. It has found use in applications such as closures, housewares and small appliances.

Formolene® 6520A meets the requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520, covering safe use of polyolefin articles and components of articles intended for direct food contact. For additional information on approved conditions of use for food contact applications, please refer to the "Products" section on our website (<http://www.fpcusa.com/ourproducts.html>).

This material is free of animal-derived content.

### Typical Properties of this Commercial Grade

| Property                                 | Test Method | Typical Values        |                       |
|------------------------------------------|-------------|-----------------------|-----------------------|
|                                          |             | English               | SI                    |
| Melt Flow Rate, I <sub>2</sub> @ 230°C   | ASTM D1238  | 20 g/10 min           | 20 g/10 min           |
| Density                                  | ASTM D1505  | 0.9 g/cm <sup>3</sup> | 0.9 g/cm <sup>3</sup> |
| Tensile Strength at Yield (50 mm/min)    | ASTM D638   | 3,500 psi             | 24 MPa                |
| Elongation at Yield (50 mm/min)          | ASTM D638   | 7 %                   | 7 %                   |
| Flexural Modulus (1.3 mm/min), 1% Secant | ASTM D790   | 165,000 psi           | 1138 MPa              |
| Notched Izod Impact Strength @ 73°F      | ASTM D256A  | 3.0 ft-lb/in          | 160 J/m               |
| Notched Izod Impact Strength @ 32°F      | ASTM D256A  | 1.7 ft-lb/in          | 91 J/m                |
| Heat Deflection Temperature @ 66 psi     | ASTM D648   | 212 °F                | 100 °C                |
| Rockwell Hardness                        | ASTM D785   | 95 R Scale            | 95 R Scale            |

Note: Specimens were injection molded according to the conditions specified in ASTM D4101.

Data for representative purposes only; not to be construed as product specification. Published 2/01, Revised 3/18

Any inquiries regarding this data sheet should be addressed to: 9 Peach Tree Hill Road • Livingston, NJ 07039 • Phone: (888) FPCUSA3 • Fax: (973) 422-7772

The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions concerning uses or applications are only the opinion of FORMOSA PLASTICS CORPORATION, U.S.A. and users should perform their own tests to determine the suitability of these products for their own particular purposes. However, because of numerous factors affecting the results, FORMOSA PLASTICS CORPORATION, U.S.A. MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, other than that the material conforms to the applicable current Standard Specifications Statements herein, therefore, should not be construed as representations or warranties. The responsibility of FORMOSA PLASTICS CORPORATION, U.S.A. for claims arising out of breach of warranty, negligence, strict liability or otherwise is limited to the purchase price of the material. Statements concerning the use of the products of formulations described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is assumed.

© Formosa Plastics Corporation, U.S.A.

Formolene® is a registered trademark of FPC USA

10/15

