



Formosa Plastics®

Formolene® PP

Formolene® 6535N

Impact Copolymer - Designed to Meet the Physical Requirements of Automotive Interior Trim

Formolene® 6535N is an engineered, medium impact copolymer polypropylene. It was specifically developed to meet the OEM demands for automotive interior trim applications, with proven injection molding economy.

The optimal stiffness and impact balance also provides for utility in industrial applications including bins and crates, and small appliances.

Material has been approved under automotive specifications - FCA MS-DB-500 CPN 3560 and CPN 4732, Ford WSS-M4D638-B, GM16208-T1, Renault Nissan AS5, and Toyota TSM 5514G Class 2.

This material is free of animal-derived content.

Typical Properties of this Commercial Grade

Property	Test Method	Typical Values	
		English	SI
Melt Flow Rate, I ₂ @ 230°C	ASTM D1238	35 g/10 min	35 g/10 min
Density	ASTM D1505	0.9 g/cm ³	0.9 g/cm ³
Tensile Strength at Yield (50 mm/min)	ASTM D638	3,500 psi	24 MPa
Elongation at Break (50 mm/min)	ASTM D638	100 %	100 %
Flexural Modulus (1.3 mm/min), 1% Secant	ASTM D790	165,000 psi	1138 MPa
Notched Izod Impact Strength @ 73°F	ASTM D256A	2.5 ft-lb/in	133 J/m
Notched Izod Impact Strength @ 32°F	ASTM D256A	1.5 ft-lb/in	80 J/m
Notched Izod Impact Strength @ 0°F	ASTM D256A	1.2 ft-lb/in	64 J/m
Heat Deflection Temperature @ 66 psi	ASTM D648	207 °F	97 °C
Heat Deflection Temperature @ 264 psi	ASTM D648	126 °F	52 °C
Hardness, Durometer Shore D	ASTM D2340	63 Shore D	

Note: Specimens injection molded according to the conditions specified in ASTM D4101. Data for representative purposes only; not to be construed as product specification. Published 9/04, Revised 3/18

Any inquiries regarding this data sheet should be addressed to: 9 Peach Tree Hill Road • Livingston, NJ 07039 • Phone: (888) FPCUSA3 • Fax: (973) 422-7772

The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions concerning uses or applications are only the opinion of FORMOSA PLASTICS CORPORATION, U.S.A. and users should perform their own tests to determine the suitability of these products for their own particular purposes. However, because of numerous factors affecting the results, FORMOSA PLASTICS CORPORATION, U.S.A. MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, other than that the material conforms to the applicable current Standard Specifications Statements herein, therefore, should not be construed as representations or warranties. The responsibility of FORMOSA PLASTICS CORPORATION, U.S.A. for claims arising out of breach of warranty, negligence, strict liability or otherwise is limited to the purchase price of the material. Statements concerning the use of the products of formulations described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is assumed.

© Formosa Plastics Corporation, U.S.A.

Formolene® is a registered trademark of FPC USA

10/15

