

Technical Data Sheet



Adstif HA802H

Polypropylene, Homopolymer

Product Description

Adstif HA802H polypropylene is available in pellet form. This resin is typically used in film, thermoforming and compounding applications requiring high stiffness and high temperature resistance.

Regulatory Status

For regulatory compliance information, see Adstif HA802H [Product Stewardship Bulletin \(PSB\) and Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	North America
Application	Containers; Specialty Film
Market	Compounding; Flexible Packaging; Rigid Packaging
Processing Method	BOPP; Compounding; Thermoforming
Attribute	High Heat Resistance; High Stiffness

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (230 °C/2.16 kg)	2.3	g/10 min	2.3	g/10 min	ASTM D1238
Density, (23 °C)	0.90	g/cm³	0.90	g/cm³	ASTM D792
Mechanical					
Flexural Modulus					
(0.05 in/min, 1% Secant, Procedure A)	275000	psi			ASTM D790
(1.3 mm/min, 1% Secant, Procedure A)			1900	MPa	ASTM D790
Tensile Strength at Yield					
(2 in/min)	5400	psi			ASTM D638
(50 mm/min)			37	MPa	ASTM D638
Tensile Elongation at Yield	8	%	8	%	ASTM D638
Impact					
Notched Izod Impact Strength					
(73 °F, Method A)	0.7	ft-lb/in			ASTM D256
(23 °C, Method A)			37	J/m	ASTM D256
Thermal					
Deflection Temperature Under Load					
(66 psi, Unannealed)	219	°F			ASTM D648
(0.45 MPa, Unannealed)			104	°C	ASTM D648



Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2026

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.

