

Technical Data Sheet

PP H235G / 1101P

Polypropylene Homopolymer



Product Description

Advanced PP H235G is a medium-flow polypropylene homopolymer fiber grade formulated for efficient processing and consistent product quality. This resin exhibits a balanced molecular weight distribution and moderate crystallinity, contributing to its excellent performance in various fiber applications. Advanced PP H235G is ideally suited to produce staple fibers, high denier bulked continuous filaments (BCF) yarn, and continuous filaments (CF) at medium line speed. Notably, this grade incorporates an advanced, phenol-free stabilizer package, ensuring exceptional resistance to gas fading.

General

Typical Application

- Continuous filaments (CF)
- Bulked continuous filaments (BCF)
- Filter Fabric

Product Features

- Controlled Flowability
- Optimized Molecular Weight Distribution
- Balanced Crystallinity
- Advanced Phenol-Free Stabilization Package

Regulatory Status

- Compliance with Reach regulation
- Compliance with FDA regulation
- Compliance with European Union Regulation (EU) 10/2011

Type	Properties	Unit	Value	Test Method
Resin	Density	g / cm ³	0.9	ISO 1183
	Melt Flow Rate (MFR)	g / 10 min	18	ISO 1133
Mechanical	Tensile Modulus	MPa	1500	ISO 527-2
	Tensile Stress at Yield	MPa	35	ISO 527-2
	Tensile Strain at Yield	%	10	ISO 527-2
	Tensile Strain at Break	%	>50	ISO 527-2
	Charpy Impact strength notched (+23°C)	KJ / m ²	2.5	ISO 179/1eA
	Ball indentation hardness (H 358/30)	MPa	70	ISO 2039-1
	Vicat Softening Temperature (A/50, 10 N)	°C	154	ISO 306
Thermal	Heat Deflection Temperature B, (45 MPa)	°C	85	ISO 75-2

