

Technical Data Sheet



Alathon L4904

High Density Polyethylene

Product Description

Alathon L4904 is a bimodal, high molecular weight, high density polyethylene resin with excellent processing characteristics. L4904 is selected by customers for pressure pipe applications including gas distribution, industrial piping, mining, oil & gas gathering, municipal water service lines and sewers. Customers typically use L4904 in applications requiring high resistance to pipe failure by rapid crack propagation and slow crack growth mechanisms. Please contact your LyondellBasell Technical Service Engineer or Sales Manager for an approved color and black masterbatch list. When L4904 is combined with a LyondellBasell approved color or black masterbatch at the correct use level, this compound may meet the following standards or requirements:

- ASTM D2513-18a for Polyethylene (PE) Gas Pressure Pipe, Tubing and Fitting, Category C per Table 5
- ASTM D3350 Cell Classifications: **PE445574C, PE445574E, PE445576C, and PE445576E**. For Oxidative Resistance Classification Categorization values (CC), please contact your LyondellBasell Technical Service Engineer or Sales Manager.
- CSA B137.1 for Pipe, Tubing, and Fittings for Cold-Water Pressure Services
- CSA B137.4 for Polyethylene Piping Systems for Gas Services: PE4710 PLUS & PE 100
- NSF Standard 14 and Standard 61 for Potable Water Pipe and Fittings
- NSF Standard 14 for Gas Distribution Applications
- NSF Standard 358-1 for PE Pipe and Fittings for "Geothermal" Heat Pump Systems
- Plastics Pipe Institute (PPI) PE4710 and PE 100 per PPI TR-3

Regulatory Status

For regulatory compliance information, see Alathon L4904 [Product Stewardship Bulletin \(PSB\) and Safety Data Sheet \(SDS\)](#).

Status	Commercial
Availability	North America; South & Central America
Application	Drainage Pipe; Drinking Water Pipe; Gas Pipe; Industrial; Soil & Waste Pipe
Market	Industrial, Building & Construction; Pipe
Processing Method	Pipe

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate					
(190 °C/5.0 kg)	0.18	g/10 min	0.18	g/10 min	ISO 1133-1
(190 °C/5.0 kg)	0.18	g/10 min	0.18	g/10 min	ASTM D1238
(190 °C/21.6 kg)	7.5	g/10 min	7.5	g/10 min	ISO 1133-1
(190 °C/21.6 kg)	7.5	g/10 min	7.5	g/10 min	ASTM D1238
Density					
(23 °C)	0.949	g/cm³	0.949	g/cm³	ASTM D1505
(23 °C)	0.949	g/cm³	0.949	g/cm³	ISO 1183-1
Mechanical					
Flexural Modulus					
(1% Secant)			1030	MPa	ISO 178
(2% Secant)	146000	psi	1006	MPa	ASTM D790
Tensile Modulus, (23 °C, 1 mm/min, Chord)			1020	MPa	ISO 527-1, -2

LyondellBasell
Technical Data Sheet
Publication Date: 7/6/2026

Page 1 of 3

Alathon L4904
Recipient Tracking #:
Request #: 7420626



Tensile Stress at Break (23 °C)	5100 psi	35.2 MPa	ASTM D638
		30 MPa	ISO 527-1, -2
Tensile Stress at Yield (23 °C)	3580 psi	24.7 MPa	ASTM D638
		24.5 MPa	ISO 527-1, -2
Tensile Elongation at Break (23 °C)	605 %	605 %	ASTM D638
	605 %	605 %	ISO 527-1, -2
PENT on Natural Resin, (2.4 MPa, 80 °C, Air)	10000 hr	10000 hr	ASTM F1473
Values were determined on natural L4904 resin.			
Thermal			
Low Temperature Brittleness, F ₅₀	<-105 °F	<-76 °C	ASTM D746
DSC Induction Temperature	500 °F	260 °C	ASTM D3350
Oxidation Induction Time, (210 °C)	>30 min	>30 min	ISO 11357-6
Oxidative-Induction Time, (200 °C)	100 min	100 min	ASTM D3895
Values were determined on L4904 compounded with an approved masterbatch.			
Conformance Testing			
Hydrostatic Design Basis			
(73 °F)	1600 psi		ASTM D2837
(140 °F)	1000 psi		ASTM D2837
Minimum Required Strength, (20 °C)		10 MPa	ISO 12162
Creep Rupture Strength			
(20 °C, 12.4 MPa)	>200 hr	>200 hr	ISO 1167-1, -2
(20 °C, 12.4 MPa)	>200 hr	>200 hr	ASTM D1598
Resistance to Rapid Crack Propagation, Pc @ 32 °F	>12 bar	>12 bar	ISO 13477
Values were obtained on 8" SDR11 pipe made with L4904 and an approved masterbatch.			
Resistance to Rapid Crack Propagation, Tc @ 5 bar	<10 °F	<-12 °C	ISO 13477
Values were obtained on 4" SDR11 pipe made with L4904 and an approved masterbatch.			
Notched Pipe Test, (80 °C, 9.2 bar)	>3000 hr	>3000 hr	ISO 13479
Values were obtained on 4" SDR11 pipe made with L4904 and an approved masterbatch.			



Notes

Typical Property values were determined on natural L4904 resin, unless otherwise noted. Conformance Test values were determined from L4904 compounded with an approved masterbatch.

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Caution

If an approved masterbatch is not used in the manufacture of pipe or fittings, the customer assumes all responsibility for determining that the final article meets the applicable material and pipe or fittings standards.

Certifications



Certified as meeting requirements of Plastics Pipe Institute and NSF International, as stated above.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2026

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.

