

Technical Data Sheet



Alathon L4904LSC

High Density Polyethylene

Product Description

Alathon L4904LSC is a bimodal, high molecular weight, high density polyethylene resin with excellent processing characteristics. L4904LSC is selected by customers for pressure pipe applications including industrial piping, mining, oil & gas gathering, municipal water service lines and sewers. Customers typically use L4904LSC in large diameter, thick wall applications requiring high resistance to pipe failure by rapid crack propagation and slow crack growth mechanisms. When L4904LSC is combined with a LyondellBasell approved color or black masterbatch at the correct use level, this compound may meet the following standards or requirements:

- ASTM D3350 Cell Classifications: **PE445574C**. For Oxidative Resistance Classification Categorization values (CC) please contact your LyondellBasell Technical Service Engineer or Sales Manager.
- NSF Standard 14 and Standard 61 for Potable Water Pipe and Fittings
- Plastic Pipe Institute (PPI) PE4710 per PPI TR-3, PE 100 Cell Classification: **PE445576C**

Regulatory Status

For regulatory compliance information, see *Alathon L4904LSC Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS)*.

Status	Commercial
Availability	North America
Application	Drainage Pipe; Drinking Water Pipe; Industrial; Soil & Waste Pipe
Market	Industrial, Building & Construction; Pipe
Processing Method	Pipe

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate					
(190 °C/5.0 kg)	0.15	g/10 min	0.15	g/10 min	ASTM D1238
(190 °C/21.6 kg)	7.5	g/10 min	7.5	g/10 min	ASTM D1238
Density, (23 °C)	0.949	g/cm ³	0.949	g/cm ³	ASTM D1505
Mechanical					
Flexural Modulus, (2% Secant)	137000	psi	945	MPa	ASTM D790
Tensile Stress at Break	4640	psi	32	MPa	ASTM D638
Tensile Stress at Yield	3550	psi	24.5	MPa	ASTM D638
Tensile Elongation at Break	550	%	550	%	ASTM D638
PENT on Natural Resin, (2.4 MPa, 80 °C, Air)	5000	hr	5000	hr	ASTM F1473
Thermal					
Low Temperature Brittleness, F ₅₀	<-96	°F	<-71	°C	ASTM D746
DSC Induction Temperature	527	°F	275	°C	ASTM D3350
Oxidative-Induction Time, (200 °C)	>110	min	>110	min	ASTM D3895
Conformance Testing					
Hydrostatic Design Basis					
(73 °F)	1600	psi			ASTM D2837
(140 °F)	1000	psi			ASTM D2837
Minimum Required Strength, (20 °C)			10	MPa	ISO 9080

LyondellBasell
Technical Data Sheet
Publication Date: 7/6/2026

Page 1 of 2

Alathon L4904LSC
Recipient Tracking #:
Request #: 7420628



Notes

Typical Property values were determined on natural L4904LSC resin, unless otherwise noted. Conformance Test values were determined from L4904LSC compounded with an approved masterbatch.

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Caution

If an approved masterbatch is not used in the manufacture of pipe or fittings, the customer assumes all responsibility for determining that the final article meets the applicable material and pipe or fittings standards.

Approved Masterbatches

Please contact your Equistar pressure pipe contact for a list of approved masterbatches and dosing levels.

Certifications



Certified as meeting requirements of Plastics Pipe Institute and NSF International, as stated above.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2026

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.

