

Technical Data Sheet



Alathon L4930TC

High Density Polyethylene

Product Description

Alathon L4930TC is a bimodal high density polyethylene copolymer natural resin used by customers for telecommunications and electrical conduits. L4930TC offers an excellent balance of stiffness, toughness and ease of processing. Conduits made with this resin are used with fiber optic cable, electrical cable and telecommunications cable. L4930TC meets the material requirements for polyethylene conduit as per ASTM F2160 and also meets the requirements of ASTM D3350 cell classifications PE435540A and PE435580A.

Regulatory Status

For regulatory compliance information, see *Alathon L4930TC* [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	Africa-Middle East; Asia-Pacific; North America
Application	Conduit
Market	Industrial, Building & Construction; Pipe
Processing Method	Pipe

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate					
(190 °C/2.16 kg)	0.34	g/10 min	0.34	g/10 min	ASTM D1238
(190 °C/21.6 kg)	32	g/10 min	32	g/10 min	ASTM D1238
Density, (23 °C)	0.949	g/cm³	0.949	g/cm³	ASTM D1505
Mechanical					
Flexural Modulus, (2% Secant)	144000	psi	993	MPa	ASTM D790
Tensile Strength at Yield	3580	psi	24.7	MPa	ASTM D638
Tensile Elongation at Break	>600	%	>600	%	ASTM D638
Environmental Stress Crack Resistance					
F ₁₀ (10% Igepal®, Cond B)	>1000	hr	>1000	hr	ASTM D1693
F ₂₀ (100% Igepal®, Cond C)	>600	hr	>600	hr	ASTM D1693
F ₅₀ (10% Igepal®, Cond B)	>1000	hr	>1000	hr	ASTM D1693
F ₅₀ (100% Igepal®, Cond B)	>1000	hr	>1000	hr	ASTM D1693
Impact					
Tensile Impact Strength	277	ft-lb/in²	582	kJ/m²	ASTM D1822
Hardness					
Shore Hardness, (Shore D)	63		63		ASTM D2240
Thermal					
Low Temperature Brittleness, F ₅₀	<-103	°F	<-75	°C	ASTM D746
DSC Induction Temperature	462	°F	239	°C	ASTM D3350



Notes

Igepal® is a registered trademark of Rhodia.

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2026

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.

