



Exelene® LDPE

Product Data Sheet

Low Density Polyethylene

Heavy Duty -LDPE

Blown Film Extrusion

0200

Melt Flow Rate **0.30**

Density **0.921**

Applications

- Greenhouse Film, Industrial Shrink Film, 25kg Industrial Bags
- Bags for re-packing powdered foods and grains such as rice, pulses, salt, sugar, flour and cereals
- Bags for packing powdered substances for domestic or industrial use such as detergents, sand and gravel

Characteristics

- The Exelene resin LDPE 0200 meets the requirements of section 177.1520, paragraph C, from chapter 21 denominated "Olefin Polymers" from the Code of Federal Regulations of the FDA, to be utilized with direct food contact.

Properties		ASTM Testing	Units	Values
Resin Properties				
Melt Flow Rate	MF ₁₂	D 1238 (190°C; 2,16 kgf)	g/10 min	0.30
Density		D 792 (23°C)	g/cm ³	0.921
Melting Point		DSC	°C	110
Blow Film Properties with thickness of 2,0 mils = 50,8 µm y BUR = 2,5				
Tensile Strength @ yield ⁽¹⁾	MD	D 882A (20 in/min)	psi	1,550
	TD		psi	1,430
Tensile Strength @ break	MD	D 882A (20 in/min)	psi	3,500
	TD		psi	3,000
Elongation @ break	MD	D 882A (20 in/min)	%	250
	TD		%	750
Flexural Strength	MD	D 882A (0,2 in/min; 1%)	psi	22,000
	TD		psi	28,000
Elmendorf Tear Propagation	MD	D 1922 (23°C; 1.600 gf)	gf	330
	TD		gf	120
Impact Resistance by the Free Falling Dart Method		D 1709A (F50; 38 mm; 66 cm)	gf	250
Opacity		D 1003	%	20.5

(1) MD = Machine Direction and TD = Transversal Direction

