



Exelene® PET

Product Data Sheet

Polyethylen Terephthalate

PET IV 84

Injection Blow Molding

PET IV 84

I.V. 0,84±.02

Melt Temp 243 ± 2

Applications

- Bottles for Carbonated Soft Drink. Food Containers

Characteristics

- The Exelene resin PET IV 84 meets the requirements of section 177.1630, paragraph C, from chapter 21 denominated "Olefin Polymers" from the Code of Federal Regulations of the FDA, to be utilized with direct food contact.

Properties	ASTM Testing	Units	Nominal Value
Resin Properties			
Melting Temperature	E1356	°C	243 ± 2
Intrinsic Viscosity	D4603	dl/g	0.84 ± 0.02
Density	D1505	g / cm	1.40
Bulk Density	D1895	kg / m	820 - 900
Acetaldehyde		ppm	1 MAX
Color - b			1 MAX
Moisture	Karl Fisher Method	wt %	0.30 MAX

<http://www.montachem.com>

