

LEXANT™ FR RESINS 905AU

REGION ASIA

DESCRIPTION

LEXAN 905AU Polycarbonate (PC) is an injection moldable non-chlorinated and non-brominated, unfilled, transparent flame retardant grade with high flow. It is UV stabilized and has an MVR of 29 (300°C/1.2kg) and a UL94 V0@2.5mm rating and is available in a variety of colors.

INDUSTRY	SUB INDUSTRY
Building and Construction	Construction
Electrical and Electronics	Electrical Devices and Displays, Electrical Components and Infrastructure

TYPICAL PROPERTY VALUES

Revision 20260509

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	64	MPa	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	86	%	ASTM D638
Tensile Modulus, 5 mm/min	2500	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	83	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2200	MPa	ASTM D790
IMPACT			
Izod Impact, notched, 23°C	700	J/m	ASTM D256
THERMAL			
Vicat Softening Temp, Rate B/50	140	°C	ASTM D1525
HDT, 1.82 MPa, 3.2mm, unannealed	125	°C	ASTM D648
CTE, -40°C to 40°C, flow	6.8E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	6.8E-05	1/°C	ASTM E831
Vicat Softening Temp, Rate B/50	140	°C	ISO 306
PHYSICAL			
Specific Gravity	1.2	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 300°C/1.2 kgf	27	g/10 min	ASTM D1238
Density	1.2	g/cm³	ISO 1183
Water Absorption, (23°C/saturated)	0.35	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.15	%	ISO 62
FLAME CHARACTERISTICS			
UL Recognized, 94V-0 Flame Class Rating	2.5	mm	UL 94

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2026 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™

