

LEXANT™ RESIN 144R

REGION AMERICAS

DESCRIPTION

LEXANT™ 144R resin is a 11 MFR polycarbonate, MVR of 12. Mold release, UL94 HB rated. This material is food contact compliant in most jurisdictions – exceptions may exist, request a declaration for details.

TYPICAL PROPERTY VALUES

Revision 20260507

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	62	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	68	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	7	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	130	%	ASTM D638
Tensile Modulus, 50 mm/min	2370	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	97	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2340	MPa	ASTM D790
Hardness, Rockwell M	70	-	ASTM D785
Hardness, Rockwell R	118	-	ASTM D785
Taber Abrasion, CS-17, 1 kg	10	mg/1000cy	ASTM D1044
Tensile Stress, yield, 50 mm/min	63	MPa	ISO 527
Tensile Stress, break, 50 mm/min	70	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	6	%	ISO 527
Tensile Strain, break, 50 mm/min	110	%	ISO 527
Tensile Modulus, 1 mm/min	2350	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	90	MPa	ISO 178
Flexural Modulus, 2 mm/min	2300	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	3204	J/m	ASTM D4812
Izod Impact, notched, 23°C	801	J/m	ASTM D256
Izod Impact, notched (natural, tints)	801	J/m	ASTM D256
Izod Impact, notched (colors)	801	J/m	ASTM D256
Tensile Impact Strength, Type S	577	kJ/m²	ASTM D1822
Falling Dart Impact (D 3029), 23°C	169	J	ASTM D3029
Instrumented Dart Impact Energy @ peak, 23°C	63	J	ASTM D3763
Izod Impact, unnotched 80°10°4 +23°C	NB	kJ/m²	ISO 180/1U
Izod Impact, unnotched 80°10°4 -30°C	NB	kJ/m²	ISO 180/1U
Izod Impact, notched 80°10°4 +23°C	12	kJ/m²	ISO 180/1A
Izod Impact, notched 80°10°4 -30°C	10	kJ/m²	ISO 180/1A
Charpy Impact, notched, 23°C	35	kJ/m²	ISO 179/2C
Charpy 23°C, Unnotch Edgew 80°10°4 sp=62mm	NB	kJ/m²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80°10°4 sp=62mm	NB	kJ/m²	ISO 179/1eU
THERMAL			
Vicat Softening Temp, Rate B/50	154	°C	ASTM D1525

© 2026 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
HDT, 0.45 MPa, 6.4 mm, unannealed	137	°C	ASTM D648
HDT, 1.82 MPa, 6.4 mm, unannealed	132	°C	ASTM D648
CTE, -40°C to 95°C, flow	6.84E-05	1/°C	ASTM E831
Specific Heat	1.25	J/g·°C	ASTM C351
Thermal Conductivity	0.19	W/m·°C	ASTM C177
Thermal Conductivity	0.2	W/m·°C	ISO 8302
CTE, 23°C to 80°C, flow	7.E-05	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate A/50	153	°C	ISO 306
Vicat Softening Temp, Rate B/50	141	°C	ISO 306
Vicat Softening Temp, Rate B/120	142	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120°10°4 sp=100mm	136	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120°10°4 sp=100mm	125	°C	ISO 75/Ae
Relative Temp Index, Elec	130	°C	UL 746B
Relative Temp Index, Mech w/impact	130	°C	UL 746B
Relative Temp Index, Mech w/o impact	130	°C	UL 746B
PHYSICAL			
Specific Gravity	1.2	-	ASTM D792
Specific Volume	0.83	cm³/g	ASTM D792
Density	1.19	g/cm³	ASTM D792
Water Absorption, (23°C/24hrs)	0.15	%	ASTM D570
Water Absorption, (23°C/Saturated)	0.35	%	ASTM D570
Water Absorption, equilibrium, 100°C	0.58	%	ASTM D570
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 300°C/1.2 kgf	10.5	g/10 min	ASTM D1238
Melt Volume Rate, MVR at 300°C/1.2 kg	12	cm³/10 min	ISO 1133
OPTICAL			
Light Transmission, 2.54 mm	88	%	ASTM D1003
Haze, 2.54 mm	1	%	ASTM D1003
Refractive Index	1.586	-	ASTM D542
ELECTRICAL			
Volume Resistivity	>1.E+17	Ω.cm	ASTM D257
Dielectric Strength, in air, 3.2 mm	14.9	kV/mm	ASTM D149
Relative Permittivity, 50/60 Hz	3.17	-	ASTM D150
Relative Permittivity, 1 MHz	2.96	-	ASTM D150
Dissipation Factor, 50/60 Hz	0.0009	-	ASTM D150
Dissipation Factor, 1 MHz	0.01	-	ASTM D150
Hot Wire Ignition {PLC}	2	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	2	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	1	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	2	PLC Code	UL 746A
Volume Resistivity	>1.E+15	Ω.cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ω	IEC 60093
Dielectric Strength, in oil, 3.2 mm	17	kV/mm	IEC 60243-1
Relative Permittivity, 1 MHz	2.7	-	IEC 60250

© 2026 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Dissipation Factor, 50/60 Hz	0.001	-	IEC 60250
Dissipation Factor, 1 MHz	0.01	-	IEC 60250
Relative Permittivity, 50/60 Hz	2.7	-	IEC 60250
FLAME CHARACTERISTICS			
UL Yellow Card Link	E121562-220863	-	-
UL Recognized, 94HB Flame Class Rating	1.47	mm	UL 94
Oxygen Index (LOI)	25	%	ASTM D2863
Oxygen Index (LOI)	25	%	ISO 4589
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	3 – 4	Hrs	
Drying Time (Cumulative)	48	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	295 – 315	°C	
Nozzle Temperature	290 – 310	°C	
Front - Zone 3 Temperature	295 – 315	°C	
Middle - Zone 2 Temperature	280 – 305	°C	
Rear - Zone 1 Temperature	270 – 295	°C	
Mold Temperature	70 – 95	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

