

LEXANT™ RESIN EM1210

REGION ASIA

DESCRIPTION

Automotive interiors. Excellent heat/impact resistance and outstanding property retention over wide temperature range/severe automotive conditions

TYPICAL PROPERTY VALUES

Revision 20200805

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	57	MPa	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	110	%	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	81	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2030	MPa	ASTM D790
IMPACT			
Izod Impact, notched, 23°C	774	J/m	ASTM D256
Izod Impact, notched, -30°C	694	J/m	ASTM D256
Izod Impact, notched, 23°C, 6.4mm	694	J/m	ASTM D256
Instrumented Dart Impact Energy @ peak, 23°C	61	J	ASTM D3763
Instrumented Dart Impact Energy @ peak, -30°C	65	J	ASTM D3763
THERMAL			
HDT, 0.45 MPa, 6.4 mm, unannealed	135	°C	ASTM D648
HDT, 1.82 MPa, 6.4 mm, unannealed	127	°C	ASTM D648
CTE, -40°C to 95°C, flow	6.48E-05	1/°C	ASTM E831
PHYSICAL			
Specific Gravity	1.19	-	ASTM D792
Water Absorption, (23°C/24hrs)	0.16	%	ASTM D570
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 300°C/1.2 kgf	13	g/10 min	ASTM D1238
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	3 – 4	Hrs	
Drying Time (Cumulative)	48	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	295 – 315	°C	
Nozzle Temperature	290 – 310	°C	
Front - Zone 3 Temperature	295 – 315	°C	
Middle - Zone 2 Temperature	280 – 305	°C	
Rear - Zone 1 Temperature	270 – 295	°C	
Mold Temperature	70 – 95	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

© 2024 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

