

LEXANT™ RESIN EX1332T

REGION EUROPE

DESCRIPTION

LEXANT™ EX1332T resin is a 3 MFR polycarbonate, MVR of 3, UV stabilized, Release agent, UL94 HB rated, It contains branched polycarbonate resin. Designed for use in multi-wall sheet or profile extrusion applications.

TYPICAL PROPERTY VALUES

Revision 20201125

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yield, 50 mm/min	65	MPa	ISO 527
Tensile Stress, break, 50 mm/min	70	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	7	%	ISO 527
Tensile Strain, break, 50 mm/min	>70	%	ISO 527
Tensile Modulus, 1 mm/min	2350	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	95	MPa	ISO 178
Flexural Modulus, 2 mm/min	2300	MPa	ISO 178
IMPACT			
Izod Impact, unnotched 80°10°3 +23°C	NB	kJ/m²	ISO 180/1U
Izod Impact, unnotched 80°10°3 -30°C	NB	kJ/m²	ISO 180/1U
Izod Impact, notched 80°10°3 +23°C	75	kJ/m²	ISO 180/1A
Izod Impact, notched 80°10°3 -30°C	55	kJ/m²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80°10°3 sp=62mm	70	kJ/m²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80°10°3 sp=62mm	50	kJ/m²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80°10°3 sp=62mm	NB	kJ/m²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80°10°3 sp=62mm	NB	kJ/m²	ISO 179/1eU
THERMAL			
Thermal Conductivity	0.2	W/m·°C	ISO 8302
CTE, 23°C to 80°C, flow	7.E-05	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	149	°C	ISO 306
Vicat Softening Temp, Rate B/120	150	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80°10°4 sp=64mm	130	°C	ISO 75/Af
PHYSICAL			
Mold Shrinkage, flow, 3.2 mm	0.5 - 0.7	%	SABIC method
Density	1.2	g/cm³	ISO 1183
Water Absorption, (23°C/saturated)	0.35	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.15	%	ISO 62
Melt Volume Rate, MVR at 300°C/1.2 kg	3	cm³/10 min	ISO 1133
Melt Volume Rate, MVR at 300°C/2.16 kg	5	cm³/10 min	ISO 1133
OPTICAL			
Light Transmission, 2.54 mm	88 - 90	%	ASTM D1003
FLAME CHARACTERISTICS			
UL Yellow Card Link	E45329-100753449	-	-

© 2024 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Glow Wire Flammability Index 850°C, passes at	1	mm	IEC 60695-2-12
MULTIWALL SHEET EXTRUSION			
Drying Temperature	120	°C	
Drying Time	2 – 4	Hrs	
Barrel - Zone 1 Temperature	260 – 300	°C	
Barrel - Zone 2 Temperature	260 – 290	°C	
Barrel - Zone 3 Temperature	260 – 290	°C	
Hopper Temperature	100 – 120	°C	
Adapter Temperature	240 – 280	°C	
Die Temperature	240 – 300	°C	
Melt Temperature	260 – 300	°C	
Calibrator Temperature	50 – 100	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

