

LEXANT™ RESIN HF1 130

REGION AMERICAS

DESCRIPTION

LEXANT™ HF1 130 resin is a 25 MFR polycarbonate, UV stabilized, UL94 V2 rated.

TYPICAL PROPERTY VALUES

Revision 20260507

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	62	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	65	MPa	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	110	%	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	93	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2300	MPa	ASTM D790
IMPACT			
Izod Impact, notched, 23°C	640	J/m	ASTM D256
Tensile Impact Strength, Type S	378	kJ/m²	ASTM D1822
Instrumented Dart Impact Energy @ peak, 23°C	54	J	ASTM D3763
THERMAL			
HDT, 1.82 MPa, 6.4 mm, unannealed	126	°C	ASTM D648
Relative Temp Index, Elec	130	°C	UL 746B
Relative Temp Index, Mech w/impact	130	°C	UL 746B
Relative Temp Index, Mech w/o impact	130	°C	UL 746B
PHYSICAL			
Specific Gravity	1.2	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 300°C/1.2 kgf	25	g/10 min	ASTM D1238
OPTICAL			
Light Transmission, 2.54 mm	88	%	ASTM D1003
Haze, 2.54 mm	1	%	ASTM D1003
FLAME CHARACTERISTICS			
UL Yellow Card Link	E121562-220946	-	-
UL Recognized, 94V-2 Flame Class Rating	1.2	mm	UL 94
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	3 – 4	Hrs	
Drying Time (Cumulative)	48	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	270 – 295	°C	
Nozzle Temperature	265 – 290	°C	
Front - Zone 3 Temperature	270 – 295	°C	
Middle - Zone 2 Temperature	260 – 280	°C	
Rear - Zone 1 Temperature	250 – 270	°C	
Mold Temperature	70 – 95	°C	

© 2026 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

