

## LEXANT™ RESIN VR2020

REGION AMERICAS

### DESCRIPTION

LEXANT™ VR2020 resin is a 18 MFR polycarbonate, MVR of 17. UV stabilized. Mold release. UL746C f1 rated. Available in transparent, limited package types, and must meet minimum order quantity requirements.

### TYPICAL PROPERTY VALUES

Revision 20260327

| PROPERTIES                                   | TYPICAL VALUES | UNITS     | TEST METHODS |
|----------------------------------------------|----------------|-----------|--------------|
| <b>MECHANICAL</b>                            |                |           |              |
| Tensile Stress, yld, Type I, 50 mm/min       | 63             | MPa       | ASTM D638    |
| Tensile Stress, brk, Type I, 50 mm/min       | 65             | MPa       | ASTM D638    |
| Tensile Strain, yld, Type I, 50 mm/min       | 7              | %         | ASTM D638    |
| Tensile Strain, brk, Type I, 50 mm/min       | 110            | %         | ASTM D638    |
| Tensile Modulus, 5 mm/min                    | 2380           | MPa       | ASTM D638    |
| Flexural Stress, yld, 1.3 mm/min, 50 mm span | 93             | MPa       | ASTM D790    |
| Flexural Modulus, 1.3 mm/min, 50 mm span     | 2300           | MPa       | ASTM D790    |
| Hardness, Rockwell M                         | 70             | -         | ASTM D785    |
| Hardness, Rockwell R                         | 120            | -         | ASTM D785    |
| Taber Abrasion, CS-17, 1 kg                  | 10             | mg/1000cy | ASTM D1044   |
| Tensile Stress, yield, 50 mm/min             | 63             | MPa       | ISO 527      |
| Tensile Stress, break, 50 mm/min             | 65             | MPa       | ISO 527      |
| Tensile Strain, yield, 50 mm/min             | 6              | %         | ISO 527      |
| Tensile Strain, break, 50 mm/min             | 100            | %         | ISO 527      |
| Tensile Modulus, 1 mm/min                    | 2350           | MPa       | ISO 527      |
| Flexural Stress, yield, 2 mm/min             | 90             | MPa       | ISO 178      |
| Flexural Modulus, 2 mm/min                   | 2300           | MPa       | ISO 178      |
| <b>IMPACT</b>                                |                |           |              |
| Izod Impact, unnotched, 23°C                 | 3204           | J/m       | ASTM D4812   |
| Izod Impact, notched, 23°C                   | 700            | J/m       | ASTM D256    |
| Tensile Impact Strength, Type S              | 546            | kJ/m²     | ASTM D1822   |
| Falling Dart Impact (D 3029), 23°C           | 169            | J         | ASTM D3029   |
| Izod Impact, notched 80°10°4 +23°C           | 12             | kJ/m²     | ISO 180/1A   |
| Izod Impact, notched 80°10°4 -30°C           | 10             | kJ/m²     | ISO 180/1A   |
| Charpy 23°C, Unnotch Edgew 80°10°4 sp=62mm   | NB             | kJ/m²     | ISO 179/1eU  |
| <b>THERMAL</b>                               |                |           |              |
| Vicat Softening Temp, Rate B/50              | 154            | °C        | ASTM D1525   |
| HDT, 0.45 MPa, 6.4 mm, unannealed            | 137            | °C        | ASTM D648    |
| HDT, 1.82 MPa, 6.4 mm, unannealed            | 132            | °C        | ASTM D648    |
| CTE, -40°C to 95°C, flow                     | 6.84E-05       | 1/°C      | ASTM E831    |
| Specific Heat                                | 1.26           | J/g·°C    | ASTM C351    |
| Thermal Conductivity                         | 0.2            | W/m·°C    | ASTM C177    |
| CTE, 23°C to 80°C, flow                      | 7.E-05         | 1/°C      | ISO 11359-2  |
| CTE, 23°C to 80°C, xflow                     | 7.E-05         | 1/°C      | ISO 11359-2  |

© 2026 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



| PROPERTIES                              | TYPICAL VALUES                 | UNITS      | TEST METHODS   |
|-----------------------------------------|--------------------------------|------------|----------------|
| Ball Pressure Test, 125°C +/- 2°C       | PASSES                         | -          | IEC 60695-10-2 |
| Ball Pressure Test, approximate maximum | 140                            | °C         | IEC 60695-10-2 |
| Vicat Softening Temp, Rate B/50         | 141                            | °C         | ISO 306        |
| Vicat Softening Temp, Rate B/120        | 141                            | °C         | ISO 306        |
| HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm | 122                            | °C         | ISO 75/Ae      |
| Relative Temp Index, Elec               | 100                            | °C         | UL 746B        |
| Relative Temp Index, Mech w/impact      | 100                            | °C         | UL 746B        |
| Relative Temp Index, Mech w/o impact    | 100                            | °C         | UL 746B        |
| <b>PHYSICAL</b>                         |                                |            |                |
| Specific Gravity                        | 1.2                            | -          | ASTM D792      |
| Specific Volume                         | 0.83                           | cm³/g      | ASTM D792      |
| Density                                 | 1.19                           | g/cm³      | ASTM D792      |
| Water Absorption, (23°C/24hrs)          | 0.15                           | %          | ASTM D570      |
| Water Absorption, (23°C/saturated)      | 0.35                           | %          | ASTM D570      |
| Water Absorption, equilibrium, 100°C    | 0.58                           | %          | ASTM D570      |
| Mold Shrinkage, flow, 3.2 mm            | 0.5 – 0.7                      | %          | SABIC method   |
| Melt Flow Rate                          |                                |            |                |
| 300°C/1.2 kgf                           | 18                             | g/10 min   | ASTM D1238     |
| Density                                 | 1.2                            | g/cm³      | ISO 1183       |
| Water Absorption, (23°C/saturated)      | 0.35                           | %          | ISO 62-1       |
| Moisture Absorption (23°C / 50% RH)     | 0.15                           | %          | ISO 62         |
| Melt Volume Rate                        |                                |            |                |
| 220°C/5.0 kg                            | 21                             | cm³/10 min | ISO 1133       |
| <b>OPTICAL</b>                          |                                |            |                |
| Light Transmission, 2.54 mm             | 88                             | %          | ASTM D1003     |
| Haze, 2.54 mm                           | 1                              | %          | ASTM D1003     |
| Refractive Index                        | 1.586                          | -          | ASTM D542      |
| <b>ELECTRICAL</b>                       |                                |            |                |
| Volume Resistivity                      | >1.E+17                        | Ω.cm       | ASTM D257      |
| Dielectric Strength, in air, 3.2 mm     | 15                             | kV/mm      | ASTM D149      |
| Relative Permittivity, 50/60 Hz         | 3.17                           | -          | ASTM D150      |
| Relative Permittivity, 1 MHz            | 2.96                           | -          | ASTM D150      |
| Dissipation Factor, 50/60 Hz            | 0.0009                         | -          | ASTM D150      |
| Dissipation Factor, 1 MHz               | 0.01                           | -          | ASTM D150      |
| Hot Wire Ignition {PLC}                 | 4                              | PLC Code   | UL 746A        |
| High Voltage Arc Track Rate {PLC}       | 2                              | PLC Code   | UL 746A        |
| High Ampere Arc Ign, surface {PLC}      | 1                              | PLC Code   | UL 746A        |
| Comparative Tracking Index (UL) {PLC}   | 2                              | PLC Code   | UL 746A        |
| <b>FLAME CHARACTERISTICS</b>            |                                |            |                |
| UL Yellow Card Link                     | <a href="#">E121562-221021</a> | -          | -              |
| UL Recognized, 94HB Flame Class Rating  | 0.76                           | mm         | UL 94          |
| UV-light, water exposure/immersion      | F1                             | -          | UL 746C        |
| <b>INJECTION MOLDING</b>                |                                |            |                |
| Drying Temperature                      | 120                            | °C         |                |
| Drying Time                             | 3 – 4                          | Hrs        |                |



| PROPERTIES                  | TYPICAL VALUES | UNITS | TEST METHODS |
|-----------------------------|----------------|-------|--------------|
| Drying Time (Cumulative)    | 48             | Hrs   |              |
| Maximum Moisture Content    | 0.02           | %     |              |
| Melt Temperature            | 280 – 305      | °C    |              |
| Nozzle Temperature          | 275 – 300      | °C    |              |
| Front - Zone 3 Temperature  | 280 – 305      | °C    |              |
| Middle - Zone 2 Temperature | 270 – 295      | °C    |              |
| Rear - Zone 1 Temperature   | 260 – 280      | °C    |              |
| Mold Temperature            | 70 – 95        | °C    |              |
| Back Pressure               | 0.3 – 0.7      | MPa   |              |
| Screw Speed                 | 40 – 70        | rpm   |              |
| Shot to Cylinder Size       | 40 – 60        | %     |              |
| Vent Depth                  | 0.025 – 0.076  | mm    |              |

### DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

