



TotalEnergies

Refining & Chemicals
Polymers

Polyethylene Lumicene® mPE M 4707 AP

Technical data sheet
Metallocene Polyethylene BLOWN FILM
Produced in Europe

Description

Lumicene® mPE M 4707 AP is a second generation metallocene based High Density Polyethylene with hexene as comonomer.

Lumicene® mPE M 4707 AP can be processed at high output rates with low extrusion pressure, excellent bubble stability and gauge control in comparison with conventional LLDPE and first generation metallocene based polyethylene. The combination of these features brings a significant downgauging potential.

Lumicene® mPE M 4707 AP is especially dedicated to film applications where high gloss and high transparency are required, particularly in blend and in coextrusion with LLDPE or LDPE.

Lumicene® mPE M 4707 AP is suited for many applications in the field of consumer, industrial, food or hygiene packaging such as bags, heavy-duty sacks, automatic packaging, mailing film and lamination.

Lumicene® mPE M 4707 AP does not contain any Polymer Processing Aid based on Perfluoroalkyl Substance (PFAS)

Characteristics

Property	Method	Unit	Typical value
Density	ISO 1183	g/cm ³	0.947
Melt Flow Rate (190°C/2.16 kg)	ISO 1133	g/10 min	0.7
Melting temperature	ISO 11357	°C	131
Vicat temperature	ISO 306	°C	130

Values indicated are typical for this product. Density and MFR are properties routinely measured during "the standard quality control procedure". The other figures are generated by tests not included in the "standard quality control procedure", and are given for information only.
Data are not intended for specification purposes.

Information contained in this publication is true and accurate at the time of publication and to the best of our knowledge. The nominal values stated herein are obtained using laboratory test specimens. These are typical values not to be construed as specification limits. Before using one of the products mentioned herein, customers and other users should take all care in determining the suitability of such product for the intended use. Unless specifically indicated, the products mentioned herein are not suitable for applications in the pharmaceutical or medical sector. The Companies within TotalEnergies Petrochemicals do not accept any liability whatsoever arising from the use of this information or the use, application or processing of any product described herein. No information contained in this publication can be considered as a suggestion to infringe patents. The Companies disclaim any liability that may be claimed for infringement or alleged infringement of patents.

TOTALENERGIES ONE TECH BELGIUM
Zone Industrielle C
B-7181 Feluy
Belgium

Rev : January 24

Page 1 of 2

www.polymers.totalenergies.com

Polyethylene





شركة بترومول للتجارة والصناعة
PETROMALL INDUSTRY & TRADING CO



TotalEnergies

Refining & Chemicals
Polymers

Polyethylene Lumicene® mPE M 4707 AP



 petromall.net

 info@petromall.ps

 +970 599 2020 64



Hebron - Palestine

فلسطين - الخليل

+972 2 2233840