

Technical Data Sheet



Moplen RP215MY B

Polypropylene, Random Copolymer

Product Description

Moplen RP215MY B is a polypropylene random copolymer designed for casting film, without anti-block and slip agent. Moplen RP215MY B is suitable for food contact.

Regulatory Status

For regulatory compliance information, see Moplen RP215MY B [Product Stewardship Bulletin \(PSB\) and Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	Asia-Pacific
Application	Food Packaging Film
Market	Flexible Packaging
Processing Method	Cast Film; Extrusion Flat-die
Attribute	Random Copolymer

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	8	g/10 min	ISO 1133-1
Mechanical			
Flexural Modulus, (23 °C)	850	MPa	ISO 178
Tensile Stress at Yield, (23 °C)	26	MPa	ISO 527-1, -2
Tensile Strain at Yield, (23 °C)	12	%	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched, (23 °C)	6	kJ/m ²	ISO 179-1/1eA
Thermal			
Vicat Softening Temperature, (A50)	133	°C	ISO 306
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	78	°C	ISO 75B-1, -2



Notes

These are typical property values not to be construed as specification limits.

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2026

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.

