

Technical Data Sheet



Microthene FN610000

Low Density Polyethylene

Product Description

Microthene F polyolefin powders are ultra-fine, spherically shaped particles with narrow size distribution suitable for use in a broad range of specialty applications. Microthene F powders combine the unique properties of a polyolefin resin with a microfine particle size.

Status	Commercial: Active
Availability	North America
Processing Method	Powders
Application	Automotive Parts; Colour Concentrates; Industrial; Interior Automotive Applications; Structural Parts

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (190 °C/2.16 kg)	5.2	g/10 min	5.2	g/10 min	ASTM D1238
Density, (23 °C)	0.923	g/cm³	0.923	g/cm³	ASTM D1505
Mechanical					
Flexural Modulus	40000	psi	275.8	MPa	ASTM D790
Tensile Strength at Break	1800	psi	12.4	MPa	ASTM D638
Tensile Elongation at Break	550	%	550	%	ASTM D638
Hardness					
Shore Hardness, (Shore D)	53		53		ASTM D2240
Thermal					
Vicat Softening Point	206.6	°F	97.0	°C	ASTM D1525
Low Temperature Brittleness	<-105	°F	<-76	°C	ASTM D746
Peak Melting Point	230.0	°F	110.0	°C	ASTM D3418
Additional Information					
Particle Shape	Spherical		Spherical		LYB Method
Average Particle Size	20	micron	20	micron	LYB Method
Particle Size Distribution	5 - 50	micron	5 - 50	micron	LYB Method
Moisture Content	<=0.1	%	<=0.1	%	LYB Method

