

Technical Data Sheet



Microthene MP625962

Linear Low Density Polyethylene

Product Description

Microthene MP625962 is a hexene LLDPE rotational molding powder with excellent flow properties selected by customers to produce a variety of objects such as toys, playground equipment, drums and agricultural and chemical storage containers. MP625962 exhibits high ESCR, low temperature impact strength and warp resistance. MP625962 is a UV-stabilized, 35-mesh powder and is also available in pellet form as *Petrothene* GA625962.

Regulatory Status

For regulatory compliance information, see *Microthene* MP625962 [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial
Availability	North America
Application	Containers; Drums; Sports, Leisure & Toys
Market	Rigid Packaging
Processing Method	Rotomolding

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (190 °C/2.16 kg)	5.0	g/10 min	5.0	g/10 min	ASTM D1238
Density, (23 °C)	0.935	g/cm³	0.935	g/cm³	ASTM D1505
Mechanical					
Flexural Modulus					
(1% Secant)	105000	psi	725	MPa	ASTM D790
(2% Secant)	91000	psi	625	MPa	ASTM D790
Tensile Strength at Yield	2700	psi	18.6	MPa	ASTM D638
Environmental Stress Crack Resistance, F ₅₀ (100% Igepal®, Cond A)	>1000	hr	>1000	hr	ASTM D1693
Impact					
Low Temperature Impact					
1/8" specimen @ -40 °F	55	ft-lbs	75	J	ARM
1/4" specimen @ -40 °F	155	ft-lbs	210	J	ARM
Thermal					
Deflection Temperature Under Load					
(66 psi, Unannealed)	131	°F	55	°C	ASTM D648
(264 psi, Unannealed)	102	°F	39	°C	ASTM D648



Notes

Tensile properties were run with a crosshead speed of 2 inches/min or 50 mm/min.

Igepal® is a registered trademark of Rhodia.

Low Temperature Impact testing was performed according to the Association of Rotational Molders (ARM) International Test Protocol.

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2026

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.

