

Technical Data Sheet



Moplen EP542T

Polypropylene, Impact Copolymer

Product Description

Moplen EP542T is a polypropylene impact copolymer manufactured, with high flowability and optimized balance of stiffness and toughness. Typical customer applications are injection molding of automotive parts, electrical appliances parts, Thin-walled packaging, and housewares like chopping boards.

Regulatory Status

For regulatory compliance information, see [Moplen EP542T Product Stewardship Bulletin \(PSB\) and Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	Africa-Middle East; Asia-Pacific; Australia and New Zealand
Application	Cooling Appliances; Dishwashing Appliances; Housewares; Opaque Containers; Washing Appliances
Market	Automotive; Consumer Products; Electrical / Electronics; Rigid Packaging
Processing Method	Injection Molding
Attribute	Good Impact Resistance; Good Strength; High Flow; Impact Copolymer

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	52	g/10 min	ASTM D1238
Density	0.90	g/cm ³	ASTM D792
Mechanical			
Flexural Modulus	1300	MPa	ASTM D790
Tensile Strength at Yield	27	MPa	ASTM D638
Tensile Elongation at Yield	5	%	ASTM D638
Impact			
Notched Izod Impact Strength			
(23 °C)	80	J/m	ASTM D256
(-20 °C)	40	J/m	ASTM D256
Hardness			
Rockwell Hardness, (R-Scale)	95		ASTM D785
Thermal			
Vicat Softening Point	150	°C	ASTM D1525
Deflection Temperature Under Load, (0.46 N/mm ²)	120	°C	ASTM D648



Notes

These are typical property values not to be construed as specification limits.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2026

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.

