

Technical Data Sheet



Moplen HP525J

Polypropylene, Homopolymer

Product Description

Moplen HP525J is a polypropylene homopolymer designed for the production of biaxially oriented polypropylene films (BOPP). The product is suitable for metallizable film, both as monolayer and in coextruded structures. It contains a standard processing stabilisation but does not contain any slip, antiblocking agents and no Calcium Stearate is intentionally added. Moplen HP525J offers good optical, easy processing and very good film profile. Typical applications are BOPP packaging films and Solid Phase Thermoforming sheets.

Regulatory Status

For regulatory compliance information, see Moplen HP525J [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	Africa-Middle East; Europe
Application	Food Packaging Film; Thermoformed Food Containers
Market	Flexible Packaging
Processing Method	BOPP; Thermoforming
Attribute	Good Processability; High Clarity; High Gloss; Homopolymer; Medium Flow; Metallizable

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	3.0	g/10 min	ASTM D1238
Density, (23 °C)	0.90	g/cm³	ASTM D792
Mechanical			
Flexural Modulus	1500	MPa	ASTM D790
Tensile Strength at Yield	33	MPa	ASTM D638
Tensile Elongation at Yield	11	%	ASTM D638
Impact			
Notched Izod Impact Strength, (34 °C)	34	J/m	ASTM D256
Thermal			
Deflection Temperature Under Load, (0.46 N/mm²)	97	°C	ASTM D648



Notes

ASTM properties above are typical values of LYB products from Asia.

These are typical property values not to be construed as specification limits.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2026

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.

