

Technical Data Sheet



Moplen RP2965

Polypropylene, Random Copolymer

Product Description

Moplen RP2965 is a polypropylene random copolymer.

Moplen RP2965 is suitable for injection moulding applications and can also be used in technical compounds. It has a medium melt flow rate and it is supplied in pelletized form.

Regulatory Status

For regulatory compliance information, see Moplen RP2965 [Product Stewardship Bulletin \(PSB\) and Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	Africa-Middle East; Europe
Application	Automotive Parts
Market	Automotive
Processing Method	Compounding; Injection Molding
Attribute	Good Chemical Resistance; Good Creep Resistance; Good Heat Resistance; Good Stiffness; Good Toughness; Low Flow

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	20	g/10 min	ISO 1133-1
Density	0.90	g/cm ³	ISO 1183-1
Mechanical			
Flexural Modulus	1430	MPa	ISO 178
Tensile Stress at Break	22.6	MPa	ISO 527-1, -2
Tensile Stress at Yield	35.4	MPa	ISO 527-1, -2
Tensile Strain at Break	630	%	ISO 527-1, -2
Tensile Strain at Yield	8.4	%	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched, (23 °C)	2.9	kJ/m ²	ISO 179
Thermal			
DSC Melting Point	153	°C	DSC



Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2026

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.

