

Technical Data Sheet



Petrothene NA350136

Ethylene Vinyl Acetate

Product Description

Petrothene NA350136 is a LDPE/EVA copolymer selected by customers for heavy-duty film packaging and other high strength, easy to seal packaging. NA350136 exhibits high impact strength and good low temperature toughness.

Regulatory Status

For regulatory compliance information, see Petrothene NA350136 [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	North America
Application	Clarity Film
Market	Flexible Packaging
Processing Method	Blown Film

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (190 °C/2.16 kg)	1.2	g/10 min	1.2	g/10 min	ASTM D1238
Base Resin Density, (23 °C)	0.926	g/cm³	0.926	g/cm³	ASTM D1505
Vinyl Acetate Content	6.6	%	6.6	%	LYB Method
Film					
Dart Drop Impact Strength, F50	285	g	285	g	ASTM D1709
Tensile Strength at Break					
MD	3250	psi	22.4	MPa	ASTM D882
TD	2750	psi	19.0	MPa	ASTM D882
Tensile Elongation at Break					
MD	190	%	190	%	ASTM D882
TD	470	%	470	%	ASTM D882
1% Secant Modulus					
MD	20000	psi	138	MPa	ASTM D882
TD	23000	psi	156	MPa	ASTM D882
Elmendorf Tear Strength					
MD	107	g	107	g	ASTM D1922
TD	83	g	83	g	ASTM D1922
Thermal					
Vicat Softening Temperature	189	°F	87	°C	ASTM D1525
Optical					
Haze	10	%	10	%	ASTM D1003
Gloss, (45°)	55		55		ASTM D2457
Additive					
Slip	800	ppm	800	ppm	LYB Method
Antiblock	4000	ppm	4000	ppm	LYB Method

LyondellBasell
Technical Data Sheet
Publication Date: 7/6/2026

Page 1 of 2

Petrothene NA350136
Recipient Tracking #:
Request #: 7422462



Notes

Data obtained from 2.0 mil (51 micron) film produced on a blown film line with a 8" (203 mm) die, 430°F (221°C) melt temperature, 2:1 BUR, 0.025" die gap at 170 lbs/hr.

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2026

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.

