

Technical Data Sheet



Petrothene NA373244

Low Density Polyethylene

Product Description

Petrothene NA373 is a series of homopolymer resins selected by customers for use in household film and other applications that require high clarity and good impact strength combined with low COF.

Regulatory Status

For regulatory compliance information, see *Petrothene NA373244* [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	North America
Application	Bags & Pouches; Clarity Film; Film Wrap; Food Packaging Film; Lamination Film; Secondary Packaging
Market	Flexible Packaging
Processing Method	Blown Film; Cast Film

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (190 °C/2.16 kg)	3.0	g/10 min	3.0	g/10 min	ASTM D1238
Base Resin Density, (23 °C)	0.924	g/cm³	0.924	g/cm³	ASTM D1505
Product Density, (23 °C)	0.927	g/cm³	0.927	g/cm³	ASTM D1505
Film					
Dart Drop Impact Strength, F50	100	g	100	g	ASTM D1709
Tensile Strength at Break					
MD	2800	psi	19.3	MPa	ASTM D882
TD	2400	psi	16.5	MPa	ASTM D882
Tensile Strength at Yield					
MD	1700	psi	12.4	MPa	ASTM D882
TD	1800	psi			ASTM D882
Tensile Elongation at Break					
MD	360	%	360	%	ASTM D882
TD	500	%	500	%	ASTM D882
1% Secant Modulus					
MD	30000	psi	207	MPa	ASTM D882
TD	33500	psi	231	MPa	ASTM D882
Elmendorf Tear Strength					
MD	320	g	320	g	ASTM D1922
TD	300	g	300	g	ASTM D1922
Optical					
Haze	9	%	9	%	ASTM D1003
Gloss	73		73		ASTM D2457
Additive					
Slip	1600	ppm	1600	ppm	LYB Method

LyondellBasell
Technical Data Sheet
Publication Date: 7/6/2026

Page 1 of 2

Petrothene NA373244
Recipient Tracking #:
Request #: 7420967



Antiblock

6000 ppm

6000 ppm

LYB Method

Product

Notes

Data obtained from 2.0 mil (51 micron) film produced on a blown film line with a 4" (102 mm) die, 370 °F (188 °C) melt temperature, 2.5:1 BUR, 0.025" die gap at 60 lbs/hr.

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2026

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.

