

Technical Data Sheet



Petrothene NA426225

Ethylene Vinyl Acetate

Product Description

Petrothene NA426225 is a LDPE/EVA copolymer resin selected by customers for applications that require easy processing and improved scaling properties.

Regulatory Status

For regulatory compliance information, see [Petrothene NA426225 Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	North America
Application	Bags & Pouches; Clarity Film; Film Wrap; Food Packaging Film; Lamination Film; Sealants; Secondary Packaging; Specialty Film; Zipper Packaging
Market	Flexible Packaging
Processing Method	Blown Film; Cast Film; Sheet and Profile Extrusion

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (190 °C/2.16 kg)	2.5	g/10 min	2.5	g/10 min	ASTM D1238
Base Resin Density, (23 °C)	0.924	g/cm³	0.924	g/cm³	ASTM D1505
Vinyl Acetate Content	2.5	%	2.5	%	LYB Method
Film					
Dart Drop Impact Strength, F50	80	g	80	g	ASTM D1709
Tensile Strength at Break					
MD	3300	psi	22.8	MPa	ASTM D882
TD	2400	psi	16.5	MPa	ASTM D882
Tensile Elongation at Break					
MD	350	%	350	%	ASTM D882
TD	550	%	550	%	ASTM D882
1% Secant Modulus					
MD	20000	psi	138	MPa	ASTM D882
TD	25000	psi	172	MPa	ASTM D882
Elmendorf Tear Strength					
MD	220	g	220	g	ASTM D1922
TD	250	g	250	g	ASTM D1922
Thermal					
Vicat Softening Temperature	194	°F	90	°C	ASTM D1525
Optical					
Haze	5.1	%	5.1	%	ASTM D1003
Gloss, (45°)	71		71		ASTM D2457
Additive					
Slip	1000	ppm	1000	ppm	LYB Method
Antiblock	1900	ppm	1900	ppm	LYB Method

LyondellBasell
Technical Data Sheet
Publication Date: 7/6/2026

Page 1 of 2

Petrothene NA426225
Recipient Tracking #:
Request #: 7422465



Processing Parameters

Melt Temperature	330 - 380 °F	166 - 194 °C
Blow-Up Ratio	1.7 - 3.0 BUR	1.7 - 3.0 BUR

Notes

Film data obtained from sample produced on a 3 1/2" (89mm) blown film line, commercially available 8" (203 mm) die, 375°F (191°C) melt extrusion temperature, 2:1 BUR, 1.25 mil (32 micron) gauge, 0.025" die gap at 130 lbs/hr.

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2026

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.

