

Technical Data Sheet



Petrothene NA952094

Low Density Polyethylene

Product Description

Petrothene NA952094 is a low density homopolymer resin selected by customers for use in industrial and consumer packaging as well as liner and bag applications. NA952094 has an excellent balance of processability, toughness and drawdown.

Regulatory Status

For regulatory compliance information, see Petrothene NA952094 [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	North America
Application	Agriculture Film; Bags & Pouches; Can Liners; Film Wrap; Food Packaging Film; Lamination Film; Liner Film; Secondary Packaging; Surface Protection Film
Market	Flexible Packaging
Processing Method	Blown Film; Cast Film

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (190 °C/2.16 kg)	2.0	g/10 min	2.0	g/10 min	ASTM D1238
Base Resin Density, (23 °C)	0.919	g/cm³	0.919	g/cm³	ASTM D1505
Product Density, (23 °C)	0.921	g/cm³	0.921	g/cm³	ASTM D1505
Mechanical					
Tensile Strength	1800	psi	12.4	MPa	ASTM D638
Tensile Elongation at Break	650	%	650	%	ASTM D638
Film					
Dart Drop Impact Strength, F50	110	g	110	g	ASTM D1709
Tensile Strength at Break					
MD	3200	psi	22.1	MPa	ASTM D882
TD	2300	psi	15.9	MPa	ASTM D882
Tensile Elongation at Break					
MD	200	%	200	%	ASTM D882
TD	500	%	500	%	ASTM D882
1% Secant Modulus					
MD	26500	psi	183	MPa	ASTM D882
TD	32000	psi	221	MPa	ASTM D882
Elmendorf Tear Strength					
MD	350	g	350	g	ASTM D1922
TD	70	g	70	g	ASTM D1922
Thermal					
Vicat Softening Temperature	185	°F	85	°C	ASTM D1525
Additive					
Slip	500	ppm	500	ppm	LYB Method



Antiblock

4000 ppm

4000 ppm

LYB Method

Product	Product Density(g/cm³)	Slip(ppm)	Antiblock (ppm)
NA952000	0.919	None	None
NA952094	0.921	500	4000

Notes

Mechanical data derived from Type IV specimen, 75 mil plaque @ 20" per minute.

Data obtained from 1.25 mil (32 micron) film produced on a blown film line with a 8" (203 mm) die, 350°F (177°C) melt temperature, 2:1 BUR, 0.025" die gap at 150 lbs/hr.

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2026

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.

