

Technical Data Sheet

Petrothene NA960070

Low Density Polyethylene

Product Description

Petrothene NA960 is a series of resins selected by customers for use in a wide variety of industrial film applications where high impact strength and excellent drawdown are needed. NA960 exhibits good uniformity, ease of processing and good tensile strength.

Regulatory Status

For regulatory compliance information, see Petrothene NA960070 [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status Commercial: Active

Availability North America

Application Agriculture Film; Bags & Pouches; Bottles and Vials; Bottles For Consumer Goods; Bottles for Industrial Use; Can Liners; Caps & Closures; Clear Containers; Film Wrap; Food Packaging Film; Lamination Film; Liner Film; Opaque Containers; Secondary Packaging; Surface Protection Film

Market Flexible Packaging

Processing Method Blown Film; Cast Film

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (190 °C/2.16 kg)	1.0	g/10 min	1.0	g/10 min	ASTM D1238
Base Resin Density, (23 °C)	0.920	g/cm³	0.920	g/cm³	ASTM D1505
Mechanical					
Tensile Strength at Break	2100	psi	14.5	MPa	ASTM D638
Tensile Elongation at Break, (23 °C)	990	%	990	%	ASTM D638
Film					
Dart Drop Impact Strength, F50	85	g	85	g	ASTM D1709
Tensile Strength at Break					
MD	5300	psi	36.5	MPa	ASTM D882
TD	3100	psi	21.4	MPa	ASTM D882
Tensile Strength at Yield					
MD	1600	psi	11.0	MPa	ASTM D882
TD	1600	psi	11.0	MPa	ASTM D882
Tensile Elongation at Break					
MD	120	%	120	%	ASTM D882
TD	620	%	620	%	ASTM D882
Tensile Elongation at Yield					
MD	7	%	7	%	ASTM D882
TD	9	%	9	%	ASTM D882
1% Secant Modulus					
MD	32000	psi	221	MPa	ASTM D882
TD	43000	psi	297	MPa	ASTM D882



Elmendorf Tear Strength			
MD	500 g	500 g	ASTM D1922
TD	100 g	100 g	ASTM D1922
Thermal			
Vicat Softening Temperature	198 °F	92 °C	ASTM D1525
Additive			
Slip	500 ppm	500 ppm	LYB Method
Antiblock	1500 ppm	1500 ppm	LYB Method

Product	Slip(ppm)	Antiblock (ppm)
NA960000	None	None
NA960070	500	1500
NA960183	None	4000

Notes

Mechanical data derived from Type IV specimen, 75 mil plaque @ 20" per minute.

Data obtained from 1.1 mil film produced on a 2" blown film line, commercially available 4" die, 350°F (177°C) melt extrusion temperature, 2:1 BUR with a 0.025" die gap at 60 lbs/hr.

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2026

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.

