

Technical Data Sheet



Pro-fax RP223L

Polypropylene, Random Copolymer

Product Description

Pro-fax RP223L is a medium melt flow rate polypropylene random copolymer available in pellet form. This resin is typically used in cast and oriented film applications. In film applications it offers exceptional clarity, gloss, improved cold temperature impact resistance and lower and broader heat sealing properties as compared to conventional polypropylene homopolymer. Pro-fax RP223L is a barefoot resin with no slip, anti-block or other property specific additives. This product is manufactured with a non-phthalate catalyst system and is produced without animal derived components.

Regulatory Status

For regulatory compliance information, see Pro-fax RP223L [Product Stewardship Bulletin \(PSB\) and Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	North America
Application	Bags & Pouches; Breathable Film; Film Wrap; Food Packaging Film; Heavy Duty Packaging; Hygiene Film; Stationery Film; Twist Wrap Film
Processing Method	Cast Film; Oriented Film
Attribute	Good Heat Seal; Good Optical Properties; Good Processability; Medium Flow

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (230 °C/2.16 kg)	7.0	g/10 min	7.0	g/10 min	ASTM D1238
Density, (23 °C)	0.90	g/cm³	0.90	g/cm³	ASTM D792
Mechanical					
Flexural Modulus					
(0.05 in/min, 1% Secant, Procedure A)	130000	psi			ASTM D790
(1.3 mm/min, 1% Secant, Procedure A)			896	MPa	ASTM D790
Tensile Strength at Yield					
(2 in/min)	3800	psi			ASTM D638
(50 mm/min)			26.2	MPa	ASTM D638
Tensile Elongation at Yield	13	%	13	%	ASTM D638
Impact					
Notched Izod Impact Strength					
(73 °F, Method A)	0.95	ft-lb/in			ASTM D256
(23 °C, Method A)			51	J/m	ASTM D256
Gardner Impact, (23 °C, Geometry GC)	160	in-lbs	18	J	ASTM D5420
Thermal					
Deflection Temperature Under Load					
(66 psi, Unannealed)	174	°F			ASTM D648
(0.45 MPa, Unannealed)			79	°C	ASTM D648



Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2026

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.

