

### Technical Data Sheet



#### Pro-fax EP549U

Polypropylene, Impact Copolymer

#### Product Description

Pro-fax EP549U high flow polypropylene impact copolymer is available in pellet form. This resin is typically used in thin-wall injection molding applications and offers very good stiffness/impact balance.

#### Regulatory Status

For regulatory compliance information, see Pro-fax EP549U [Product Stewardship Bulletin \(PSB\) and Safety Data Sheet \(SDS\)](#).

|                          |                                                         |
|--------------------------|---------------------------------------------------------|
| <b>Status</b>            | Commercial: Active                                      |
| <b>Availability</b>      | North America                                           |
| <b>Application</b>       | TWIM Food Containers                                    |
| <b>Market</b>            | Rigid Packaging                                         |
| <b>Processing Method</b> | Injection Molding                                       |
| <b>Attribute</b>         | Contains Antistat; Good Stiffness; High Flow; Nucleated |

| Typical Properties                    | Nominal Value | English Units     | Nominal Value | SI Units          | Test Method |
|---------------------------------------|---------------|-------------------|---------------|-------------------|-------------|
| <b>Physical</b>                       |               |                   |               |                   |             |
| Melt Flow Rate, (230 °C/2.16 kg)      | 80            | g/10 min          | 80            | g/10 min          | ASTM D1238  |
| Density, (23 °C)                      | 0.90          | g/cm <sup>3</sup> | 0.90          | g/cm <sup>3</sup> | ASTM D792   |
| <b>Mechanical</b>                     |               |                   |               |                   |             |
| Flexural Modulus                      |               |                   |               |                   |             |
| (0.05 in/min, 1% Secant, Procedure A) | 180000        | psi               |               |                   | ASTM D790   |
| (1.3 mm/min, 1% Secant, Procedure A)  |               |                   | 1240          | MPa               | ASTM D790   |
| Tensile Strength at Yield             |               |                   |               |                   |             |
| (2 in/min)                            | 3500          | psi               |               |                   | ASTM D638   |
| (50 mm/min)                           |               |                   | 24            | MPa               | ASTM D638   |
| Tensile Elongation at Yield           | 4             | %                 | 4             | %                 | ASTM D638   |
| <b>Impact</b>                         |               |                   |               |                   |             |
| Notched Izod Impact Strength          |               |                   |               |                   |             |
| (73 °F, Method A)                     | 1.7           | ft-lb/in          |               |                   | ASTM D256   |
| (23 °C, Method A)                     |               |                   | 91            | J/m               | ASTM D256   |
| <b>Thermal</b>                        |               |                   |               |                   |             |
| Deflection Temperature Under Load     |               |                   |               |                   |             |
| (66 psi, Unannealed)                  | 226           | °F                |               |                   | ASTM D648   |
| (0.45 MPa, Unannealed)                |               |                   | 108           | °C                | ASTM D648   |



### Notes

These are typical property values not to be construed as specification limits.

### Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

### Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2026

### Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

### Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.

