

SABIC® LDPE 1905U0

LOW DENSITY POLYETHYLENE

DESCRIPTION

SABIC® LDPE 1905U0 is an Ultra Melt Strength (UMS) grade typically used in foam applications.

Application

SABIC® LDPE 1905U0 can be typically used for all types of foam, produced with chemical blowing agents or physical gases, X-linked and non X-linked.

This product is not intended for and must not be used in any pharmaceutical/medical applications.

TYPICAL PROPERTY VALUES

Revision 20260305

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate (MFR)			
at 190 °C and 2.16 kg	5	dg/min	ISO 1133
Density	920	kg/m³	ASTM D1505
MECHANICAL PROPERTIES			
Modulus of elasticity	240	MPa	SABIC method
Hardness Shore D	44	-	ISO 868
THERMAL PROPERTIES			
Vicat Softening Temperature			
at 10 N (VST/A)	88	°C	ISO 306
DSC test			
melting point	105	°C	DIN 53765
crystallization temperature	94	°C	DIN 53765
avg. heat of fusion	100	J/g	DIN 53765

STORAGE AND HANDLING

Polyethylenes resins (in pelletised or powder form) should be stored in such a way that it prevents exposure to direct sunlight and/or heat, as this may lead to quality deterioration. The storage location should also be dry, dust free and the ambient temperature should not exceed 50 °C. Not complying with these precautionary measures can lead to a degradation of the product which can result in colour changes, bad smell and inadequate product performance. It is also advisable to process polyethylene resins (in pelletised or powder form) within 6 months after delivery, this because also excessive aging of polyethylene can lead to a deterioration in quality.

ENVIRONMENT AND RECYCLING

The environmental aspects of any packaging material do not only imply waste issues but have to be considered in relation with the use of natural resources, the preservations of foodstuffs, etc. SABIC considers polyethylene to be an environmentally efficient packaging material. Its low specific energy consumption and insignificant emissions to air and water designate polyethylene as the ecological alternative in comparison with the traditional packaging materials. Recycling of packaging materials is supported by SABIC whenever ecological and social benefits are achieved and where a social infrastructure for selective collecting and sorting of packaging is fostered. Whenever 'thermal' recycling of packaging (i.e. incineration with energy recovery) is carried out, polyethylene -with its fairly simple molecular structure and low amount of additives- is considered to be a trouble-free fuel.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2026 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™

