

SABIC® LLDPE RVL5056

LINEAR LOW DENSITY POLYETHYLENE

DESCRIPTION

SABIC® LLDPE RVL5056 is a hexene linear low density polyethylene that provides good stress crack resistance, rigidity, toughness and easy procesability. This resin is typically used for rotational molding of large industrial and agricultural tanks, trash containers and chemical storage containers.

SABIC® LLDPE RVL5056 is formulated with an UV-stabilization package, which can be suitable for outdoor applications and is supplied in pelletized form. It is recommended that SABIC® LLDPE RVL5056 is grinded before use in rotational molding applications.

This product is not intended for and must not be used in any pharmaceutical/medical applications.

TYPICAL PROPERTY VALUES

Revision 20260224

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate (MFR)			
at 190 °C and 2.16 kg	3.5	dg/min	ISO 1133
Density	938	kg/m³	ISO 1183
MECHANICAL PROPERTIES			
Tensile test ^{(1) (2)}			
Stress at yield	19	MPa	ISO 527-2
Strain at break	>800	%	ISO 527-2
Tensile modulus	670	MPa	ISO 527-2
Flexural test			
Flexural modulus	820	MPa	ISO 178
Flexural strength	20	MPa	ISO 178
Charpy Impact Strength Notched			
at 23 °C	13	kJ/m²	ISO 179/1eA
Hardness Shore D	57	-	ISO 868
ESCR (100% Igepal CO-630), F50	>1000	h	ASTM D1693B
THERMAL PROPERTIES			
Heat deflection temperature			
at 0.45 MPa (HDT/B)	58	°C	ISO 75-2
at 1.80 MPa (HDT/A)	39	°C	ISO 75-2
Vicat Softening Temperature ^{(3) (4)}			
at 10 N (VST/A)	117	°C	ISO 306
DSC test			
melting point	126	°C	ISO 11357-3

(1) Test specimen according to ISO 527-2 type 1BA, thickness 3 mm

(2) Speed of testing: 50 mm/min

(3) Compression moulding of test specimen at 180°C according to ISO 17855-2

(4) Conditioning of test specimen: temp. 23 °C, relative humidity 50 %, 24 hours

© 2026 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



STORAGE AND HANDLING

Polyethylenes resins (in pelletised or powder form) should be stored in such a way that it prevents exposure to direct sunlight and/or heat, as this may lead to quality deterioration. The storage location should also be dry, dust free and the ambient temperature should not exceed 50 °C. Not complying with these precautionary measures can lead to a degradation of the product which can result in colour changes, bad smell and inadequate product performance. It is also advisable to process polyethylene resins (in pelletised or powder form) within 6 months after delivery, this because also excessive aging of polyethylene can lead to a deterioration in quality.

ENVIRONMENT AND RECYCLING

The environmental aspects of any packaging material do not only imply waste issues but have to be considered in relation with the use of natural resources, the preservations of foodstuffs, etc. SABIC considers polyethylene to be an environmentally efficient packaging material. Its low specific energy consumption and insignificant emissions to air and water designate polyethylene as the ecological alternative in comparison with the traditional packaging materials. Recycling of packaging materials is supported by SABIC whenever ecological and social benefits are achieved and where a social infrastructure for selective collecting and sorting of packaging is fostered. Whenever 'thermal' recycling of packaging (i.e. incineration with energy recovery) is carried out, polyethylene -with its fairly simple molecular structure and low amount of additives- is considered to be a trouble-free fuel.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

