

SABIC® POM 30RE

POLYOXYMETHYLENE

DESCRIPTION

SABIC® POM 30RE is a special grade for Rods and Extrusion sheet applications free of center porosity in large diameter and thickness.

TYPICAL PROPERTY VALUES

Revision 20220619

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL PROPERTIES ⁽¹⁾			
Tensile modulus (1mm/min)	2400	MPa	ISO 527-2 1A
Tensile stress at yield (50mm/min)	61	MPa	ISO 527-2 1A
Tensile strain at yield (50mm/min)	11	%	ISO 527-2 1A
Flexural modulus (23°C)	2500	MPa	ISO 178
Charpy notched impact strength @ 23°C	8.5	kJ/m ²	ISO 179/1eA
THERMAL PROPERTIES ⁽¹⁾			
Flammability Rating, UL 94			
@ 1.5mm and 3mm thickness	HB	Class	UL Tested
Melting temperature (10 °C/min)	163	°C	ISO 11357-1/-3
Deflection temperature under load DTUL (@ 1.8 MPa)	91	°C	ISO 75-1&2
PHYSICAL PROPERTIES ⁽¹⁾			
Density	1410	kg/m ³	ISO 1183
Melt volume rate (MVR)	2.5	cm ³ /10 min	ISO 1133

(1) Typical values; not to be construed as specification limits

CHARACTERISTICS

SABIC® POM 30RE has the following:

- High Strength and impact toughness.
- Good inherent lubricity and low wear.
- Good chemical resistance.

PROCESSING CONDITIONS

Drying normally it's not required, however it may be necessary to prevent splay and odor problem.

Drying time : 3 h.

Drying temperature : 80 – 100 °C

Profile Extrusion

Standard extruders with grooved feed zone and short compression screws (min. 25D) are recommended

Melt Temperature : 180 – 190 °C

STORAGE AND HANDLING

Handle in accordance with good industrial hygiene and safety practices. Provide for appropriate exhaust ventilation and dust collection at machinery. Minimize dust generation and accumulation. Routine housekeeping should be instituted to ensure that dusts do not accumulate on surfaces. Dry powders can build static electricity charges when subjected to the friction of transfer and mixing operations. Provide adequate precautions, such as electrical grounding and bonding, or inert atmospheres. Open containers only in well-ventilated area. Store in a dry and cool area. Keep away from heat sources and sources of ignition. Keep away from direct sunlight. Residual monomer vapors can accumulate in the head space of closed containers.

© 2026 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

