

SABIC® PP RELY 61EK61PS

PP IMPACT COPOLYMER

DESCRIPTION

This impact copolymer has a high molecular weight and is provided with a long-term heat stabilisation package. It exhibits extra high stiffness in combination with very high impact strength even at low temperatures. This material is typically used for extrusion of non-pressure sewage pipe applications and can also be typically used for blow-moulding of large containers and sheet extrusion.

Health, Safety and Food Contact regulations:

Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site <http://www.SABIC.com>

IMDS 80775790

TYPICAL PROPERTY VALUES

Revision 20260217

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate (MFR)			
at 230 °C and 2.16 kg	0.30	dg/min	ISO 1133
Density	905	kg/m³	ASTM D1505
FORMULATION			
Anti static agent	□	-	-
MECHANICAL PROPERTIES			
Tensile test			
strain at yield ⁽¹⁾	8	%	ISO 527-2 1A
tensile modulus ⁽²⁾	1850	MPa	ISO 527-2 1A
stress at yield	40	MPa	ISO 527-2 1A
Izod impact notched			
at 0 °C	20	kJ/m²	ISO 180/1A
at -20 °C	5	kJ/m²	ISO 180/1A
Izod impact notched			
at 23 °C	No Break	kJ/m²	ISO 180/1A
Charpy Impact Strength Notched			
at -20 °C	6	kJ/m²	ISO 179/1eA
at 0 °C	10	kJ/m²	ISO 179/1eA
Charpy impact unnotched			
at 23 °C	No Break	kJ/m²	ISO 179/1eU
Hardness Shore D	70	-	ISO 868
THERMAL PROPERTIES			
Vicat Softening Temperature ⁽³⁾			
at 50 N (VST/B)	80	°C	ISO 306
at 10 N (VST/A)	155	°C	ISO 306
OIT 200°C	>100	Minutes	EN 728



- (1) Speed of testing: 50 mm/min
- (2) Speed of testing: 1 mm/min
- (3) Temperature rate: 120°C/h

STORAGE AND HANDLING

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and /or high humidity as this could well speed up alteration and consequently loss of quality of the material and /or its packaging. Keep material completely dry for good processing.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

