

SABIC® PP-UMS 561P

PP HOMOPOLYMER

DESCRIPTION

SABIC® PP-UMS 561P is an unique new Ultra Melt Strength resin in the market, with a melt strength of more than 65 cN and outstanding foam-ability. It can be used by all industry segments as a building block to develop new foaming solutions that enable an unprecedented level of light weighting.

As SABIC® PP-UMS 561P is a non stabilized PP, please evaluate whether your use of our product requires the addition of a stabilization package.

TYPICAL PROPERTY VALUES

Revision 20260305

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate (MFR)			
at 230 °C and 2.16 kg	2.5	dg/min	ISO 1133
Density	905	kg/m³	ASTM D1505
MECHANICAL PROPERTIES			
Tensile test			
tensile modulus ⁽¹⁾	1925	MPa	ISO 527-2 1A
strain at break ⁽²⁾	15	%	ISO 527-2 1A
Izod impact notched			
at 23 °C	2.2	kJ/m²	ISO 180/1A
Melt Strength	≥65	cN	SABIC method
THERMAL PROPERTIES			
Heat deflection temperature ⁽³⁾			
at 0.45 MPa (HDT/B)	110	°C	ISO 75

(1) Speed of testing: 1 mm/min

(2) Speed of testing: 50 mm/min

(3) Flat wise (testbar 80*10*4mm)

STORAGE AND HANDLING

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and /or high humidity as this could well speed up alteration and consequently loss of quality of the material and /or its packaging. To avoid deterioration in quality, keep the material completely dry and process the material within 6 months after delivery.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

