

SABIC® PP 5271K

POLYPROPYLENE HOMOPOLYMER FOR SHEET & THERMOFORMING

DESCRIPTION

SABIC® PP5271K is a high crystallinity polypropylene homopolymer grade specifically developed for in-line and off-line thermoforming applications. SABIC® PP 5271K encompasses the following features: very high stiffness, very good clarity, very high heat distortion temperature, very good dimensional stability, good processability and fast molding cycle.

TYPICAL APPLICATIONS

SABIC® PP5271K is suitable for the production of high transparency cups, trays, lids and various containers with high stiffness.

TYPICAL PROPERTY VALUES

Revision 20211206

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES ⁽¹⁾			
Melt Flow Rate (MFR)			
@ 230°C & 2.16 kg load	3	g/10 min	ASTM D1238
Density			
@ 23°C	905	kg/m³	ASTM D792
MECHANICAL PROPERTIES ⁽²⁾			
Tensile Strength at Yield	38	MPa	ASTM D638
Tensile Elongation at Yield	8	%	ASTM D638
Flexural Modulus (1% Secant)	2000	MPa	ASTM D790 A
Notched Izod Impact Strength at 23°C	30	J/m	ASTM D256
Rockwell Hardness, R-Scale	103	-	ASTM D785
OPTICAL PROPERTIES			
Haze, 1 mm	17	%	ASTM D1003
THERMAL PROPERTIES			
Vicat Softening Point	155	°C	ASTM D1525
Heat Deflection Temperature at 455kPa	120	°C	ASTM D648

(1) Typical values; not to be construed as specification limits.

(2) Based on injection molded specimens

STORAGE AND HANDLING

Polypropylene resin should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably do not exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PP resin within 6 months after delivery.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2024 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™

