

SABIC® PP 642NH-66408

POLYPROPYLENE RANDOM CO-POLYMER FOR PIPE

DESCRIPTION

SABIC® PP 642NH-66408 is a high molecular weight, low melt flow rate polypropylene random copolymer (PP-R) green coloured and specially designed for transport of hot and cold drinking water. This grade is highly heat stabilized and specially formulated for extraction resistance with improved throughput & gloss. SABIC® PP 642NH-66408 is pre-color compounded version of SABIC® PP 651H PPR resin (Exova – MRS classification 8 MPa). SABIC® PP 642NH-66408 is a designated pipe grade.

TYPICAL APPLICATIONS

SABIC® PP 642NH-66408 is a designated pipe grade.

TYPICAL PROPERTY VALUES

Revision 20230511

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Flexural Modulus ⁽¹⁾	1040	MPa	ISO 178
POLYMER PROPERTIES			
Melt Flow Rate (MFR)			
at 230 °C and 2.16 kg	0.3	g/10 min	ISO 1133
Density	900	kg/m³	ASTM D1505
Filler content ⁽²⁾	0.5	%	SABIC method
Mould shrinkage			
24 hours after injection moulding ⁽²⁾	2.0	%	SABIC method
MECHANICAL PROPERTIES			
Tensile test			
Tensile modulus	1000	MPa	ISO 527/1A
tensile strength	28	MPa	ISO 527/1A
stress at break	18	MPa	ISO 527/1A
strain at break	70	MPa	ISO 527/1A
Izod impact notched			
at 23 °C ⁽¹⁾	26	kJ/m²	ISO 180/1A
at 0 °C	3.5	kJ/m²	ISO 180/1A
at -20 °C	2.5	kJ/m²	ISO 180/1A
THERMAL PROPERTIES			
Heat deflection temperature			
HDT A (at 1.8 MPa)	49	°C	ISO 75
HDT B (at 0.45 MPa)	84	°C	ISO 75
Coeff. of linear thermal expansion			
CLTE -30 °C to 80 °C	126	µm/mK	ASTM D696

(1) Injection molded sample ISO527-1A.

(2) Injection molded plaque 65x65x3.2 mm

© 2024 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

