

SABIC® PP FPH50

PP HOMOPOLYMER FLOWPACT

DESCRIPTION

SABIC® PP FPH50 is a grade developed for thin wall packaging as well as the caps & closures market. The grade is nucleated and is characterised by a high crystallisation temperature, excellent flow behaviour in combination with a high stiffness. SABIC® PP FPH50 allows for very cost efficient processing on the basis of easy mould filling, very shortcycle times and robust processing behaviour in combination with pigments. It has a very good antistatic performance and shows easy demoulding.

Application:

SABIC® PP FPH50 is typically used in thin wall packing applications both for food and non-food segments. In caps and closure, the grade could be used for wide mouth caps, amongst others. In media packaging, the grade offers opportunities for cycle time optimisation. The grade has excellent heat deflection temperature making it particularly be used for hot fill applications.

Health, Safety and Food Contact regulations:

Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site <http://www.sabic.com>. This product is not intended for and must not be used in any pharmaceutical/medical applications.

This grade material is UL registered under File E111275 (www.ul.com) / IMDS 7172624

TYPICAL PROPERTY VALUES

Revision 20230111

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate (MFR)			
at 230 °C and 2.16 kg	50	dg/min	ISO 1133
Density	905	kg/m³	ASTM D1505
FORMULATION			
Anti static agent	☑	-	-
Nucleating agent	☑	-	-
MECHANICAL PROPERTIES			
Tensile test			
tensile modulus ⁽¹⁾	2050	MPa	ISO 527-2 1A
stress at yield ⁽²⁾	39	MPa	ISO 527-2 1A
strain at yield	7	%	ISO 527-2 1A
Izod impact notched			
at 23 °C	2.5	kJ/m²	ISO 180/1A
Charpy Impact Strength Notched			
at 23 °C	3.0	kJ/m²	ISO 179/1eA
Hardness Shore D	71	-	ISO 868
THERMAL PROPERTIES			
Heat deflection temperature ⁽³⁾			
at 0.45 MPa (HDT/B)	105	°C	ISO 75
at 1.80 MPa (HDT/A)	60	°C	ISO 75
Vicat Softening Temperature ⁽⁴⁾			
at 10 N (VST/A)	154	°C	ISO 306
at 50 N (VST/B)	103	°C	ISO 306

© 2024 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



- (1) Speed of testing: 1 mm/min
- (2) Speed of testing: 50 mm/min
- (3) Flat wise (testbar 80*10*4mm)
- (4) Temperature rate: 120°C/h

STORAGE AND HANDLING

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and /or high humidity as this could well speed up alteration and consequently loss of quality of the material and /or its packaging. Keep material completely dry for good processing.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY. NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

