

## SABIC® PPCOMPOUND 108CS20

PP COMPOUND MINERAL FILLED IMPACT MODIFIED

### DESCRIPTION

SABIC® PPcompound 108CS20 is a material with good flow, impact and stiffness. The material is part of the SABIC® PP CS systems and also available as a CS system: using a mixture of 60% SABIC® PP 108MF10 and 40% SABIC® PPcompound 20MBT yields similar properties as listed below.

SABIC® PPcompound 108CS20 is a designated automotive grade.

IMDS ID: 111851732

### TYPICAL PROPERTY VALUES

Revision 20260217

| PROPERTIES                                  | TYPICAL VALUES | UNITS  | TEST METHODS |
|---------------------------------------------|----------------|--------|--------------|
| <b>POLYMER PROPERTIES</b>                   |                |        |              |
| <b>Melt Flow Rate (MFR)</b>                 |                |        |              |
| at 230 °C and 2.16 kg                       | 7              | dg/min | ISO 1133     |
| <b>Density</b> <sup>(1)</sup>               | 1040           | kg/m³  | ISO 1183     |
| <b>Filler content</b>                       | 20             | %      | SABIC method |
| <b>Mould shrinkage</b> <sup>(2)</sup>       |                |        |              |
| 24 hours after injection moulding           | 0.9            | %      | SABIC method |
| <b>MECHANICAL PROPERTIES</b> <sup>(1)</sup> |                |        |              |
| <b>Tensile test</b>                         |                |        |              |
| Tensile modulus                             | 1500           | MPa    | ISO 527/1A   |
| stress at yield                             | 20             | MPa    | ISO 527/1A   |
| stress at break                             | 17             | MPa    | ISO 527/1A   |
| strain at break                             | 100            | %      | ISO 527/1A   |
| <b>Flexural test</b>                        |                |        |              |
| Flexural modulus                            | 1500           | MPa    | ISO 178/1A   |
| <b>Izod impact notched</b> <sup>(3)</sup>   |                |        |              |
| at 23 °C                                    | N.B.           | kJ/m²  | ISO 180/1A   |
| at 0 °C                                     | 25             | kJ/m²  | ISO 180/1A   |
| at -20 °C                                   | 7              | kJ/m²  | ISO 180/1A   |
| <b>Charpy Impact Strength Notched</b>       |                |        |              |
| at 23 °C                                    | N.B.           | kJ/m²  | ISO 179/1eA  |
| <b>Charpy impact unnotched</b>              |                |        |              |
| at -40 °C                                   | NB             | kJ/m²  | ISO 179/1eU  |
| <b>THERMAL PROPERTIES</b> <sup>(1)</sup>    |                |        |              |
| <b>Heat deflection temperature</b>          |                |        |              |
| at 0.45 MPa (HDT/B)                         | 110            | °C     | ISO 75       |
| <b>Coeff. of linear thermal expansion</b>   |                |        |              |
| -30 °C to 100 °C                            | 80             | µm/mK  | ISO 11359-2  |

(1) Injection molded sample ISO527-1A

(2) Injection molded plaque 65x65x3.2mm

(3) N.B.: No Break

© 2026 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



### STORAGE AND HANDLING

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and/or high humidity as this could well speed up alteration and consequently loss of quality of the material and/or its packaging. Keep material completely dry for good processing.

### DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

PETROMALL

