

SABIC® PPCOMPOUND 642NH

PP COMPOUND IMPACT MODIFIED

DESCRIPTION

SABIC® PP compound PP642NH is a high molecular weight, low melt flow rate polypropylene random copolymer (PP-R), green color & specially designed for transport of hot and cold drinking water. This grade is highly heat Stabilized and specially formulated for extraction resistance with improved throughput & gloss.

SABIC® PP compound PP 642NH is a designated pipe grade

TYPICAL PROPERTY VALUES

Revision 20260224

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate (MFR)			
at 230 °C and 2.16 kg	0.3	dg/min	ISO 1133
Density ⁽¹⁾	900	kg/m³	ISO 1183
Filler content	0.5	%	SABIC method
Mould shrinkage ⁽²⁾			
24 hours after injection moulding	2	%	SABIC method
MECHANICAL PROPERTIES ⁽¹⁾			
Tensile test			
Tensile modulus	1000	MPa	ISO 527/1A
stress at yield	28	MPa	ISO 527/1A
stress at break	18	MPa	ISO 527/1A
strain at break	70	%	ISO 527/1A
Flexural test			
Flexural modulus	1040	MPa	ISO 178/1A
Izod impact notched ⁽³⁾			
at 23 °C	26	kJ/m²	ISO 180/1A
at -20 °C	2.5	kJ/m²	ISO 180/1A
Charpy Impact Strength Notched			
at 23 °C	-	kJ/m²	ISO 179/1eA
THERMAL PROPERTIES ⁽¹⁾			
Heat deflection temperature			
at 0.45 MPa (HDT/B)	84	°C	ISO 75

(1) Injection molded sample ISO527-1A

(2) Injection molded plaque 65x65x3.2mm

(3) N.B.: No Break

STORAGE AND HANDLING

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and/or high humidity as this could well speed up alteration and consequently loss of quality of the material and/or its packaging. Keep material completely dry for good processing.

© 2026 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.



petromall.net



info@petromall.ps



+970 599 2020 64



Hebron - Palestine

فلسطين - الخليل

+972 2 2233840

