

SABIC® PPCOMPOUND F9015

PP COMPOUND MINERAL FILLED IMPACT MODIFIED

DESCRIPTION

Preliminary datasheet

SABIC® PPcompound F9015 is an elastomer-modified mineral filled Polypropylene for automotive interior applications. This material has been designed to combine a good performance profile with good processing. This material is designed for intended use in foamed interior applications. Datasheet values are based on standard, solid specimen.

SABIC® PPcompound F9015 is a designated automotive grade.

IMDS ID:963562131

TYPICAL PROPERTY VALUES

Revision 20260316

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate (MFR)			
at 230 °C and 2.16 kg	20	dg/min	ISO 1133
Density ⁽¹⁾	1010	kg/m³	ISO 1183
Filler content	15	%	SABIC method
Mould shrinkage ⁽²⁾			
24 hours after injection moulding	0.9	%	SABIC method
MECHANICAL PROPERTIES ^{(1) (3)}			
Tensile			
Tensile modulus	1750	MPa	ISO 527/1A
stress at yield	20	MPa	ISO 527/1A
stress at break	15	MPa	ISO 527/1A
strain at break	6	%	ISO 527/1A
Flexural test			
Flexural modulus	1730	MPa	ISO 178/1A
Charpy impact unnotched			
at 23 °C	-	kJ/m²	ISO 179/1eU
at 0 °C	-	kJ/m²	ISO 179/1eU
at -30 °C	-	kJ/m²	ISO 179/1eU
Charpy Impact Strength Notched ⁽⁴⁾			
at 23 °C	-	kJ/m²	ISO 179/1eA
at 0 °C	-	kJ/m²	ISO 179/1eA
at -30 °C	-	kJ/m²	ISO 179/1eA
Izod impact notched ⁽⁴⁾			
at 23 °C	N.B.	kJ/m²	ISO 180/1A
at 0 °C	10	kJ/m²	ISO 180/1A
THERMAL PROPERTIES ⁽¹⁾			
Heat deflection temperature			
at 1.8 MPa (HDT/A)	57	°C	ISO 75
at 0.45 MPa (HDT/B)	100	°C	ISO 75

© 2026 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Coeff. of linear thermal expansion			
-30 °C to 100°C	76	µm/mK	ISO 11359-2
(1) Injection molded sample ISO527-1A (2) Injection molded plaque 65x65x3.2mm (3) N.B.: No Break (4) U-shaped notch; N.B.: No Break			

STORAGE AND HANDLING

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and/or high humidity as this could well speed up alteration and consequently loss of quality of the material and/or its packaging. Keep material completely dry for good processing.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

