

## SABIC® VESTOLEN A RELY 5922R 10000 BLACK

HIGH DENSITY POLYETHYLENE

### DESCRIPTION

SABIC® Vestolen A RELY 5922R 10000 is a grade which has a high density and a bimodal distribution of the molecular mass. Due to its resistance against slow crack growth (SCG) the material SABIC® Vestolen A RELY 5922R 10000 is considered as PE100-RC and may be used for no dig applications. Moreover it may be used for the production of thick walled (large diameter and low SDR) pipes for infrastructure and industrial application due to its low sagging characteristics and it shows favorable processing behavior. This material meets (inter)national standards for use in gas, drinking water and waste water piping. MRS class ISO 12162 MPa = 10.0 (PE 100).

This product is not intended for and must not be used in any pharmaceutical/medical applications.

### TYPICAL PROPERTY VALUES

Revision 20260216

| PROPERTIES                                        | TYPICAL VALUES | UNITS   | TEST METHODS |
|---------------------------------------------------|----------------|---------|--------------|
| <b>POLYMER PROPERTIES</b>                         |                |         |              |
| Colour                                            | Black          | -       | -            |
| RAL number                                        | 9004           | -       | -            |
| <b>Melt Flow Rate (MFR)</b>                       |                |         |              |
| at 190 °C and 5 kg                                | 0.2            | dg/min  | ISO 1133     |
| Carbon black content                              | 2.25           | %       | ISO 6964     |
| Density                                           | 959            | kg/m³   | ISO 1183     |
| <b>MECHANICAL PROPERTIES</b>                      |                |         |              |
| <b>Tensile test</b> <sup>(1) (2)</sup>            |                |         |              |
| stress at yield                                   | 24             | MPa     | ISO 527-2    |
| strain at yield                                   | 9              | %       | ISO 527-2    |
| tensile modulus                                   | 1100           | MPa     | ISO 527-2    |
| <b>Charpy Impact Strength Notched</b>             |                |         |              |
| at 23 °C                                          | 26             | kJ/m²   | ISO 179/1eA  |
| at -30 °C                                         | 10             | kJ/m²   | ISO 179/1eA  |
| Hardness Shore D                                  | 62             | -       | ISO 868      |
| ESCR FNCT <sup>(3)</sup>                          | >8760          | h       | ISO 16770    |
| ESCR (Strain Hardening), Gp <sup>(4)</sup>        | >50            | MPa     | SABIC method |
| MRS classification                                | 10             | MPa     | ISO 12162    |
| Notch Pipe Test                                   | >8760          | h       | EN ISO 13479 |
| OIT 210 °C                                        | >20            | Minutes | ISO 11357-6  |
| <b>THERMAL PROPERTIES</b>                         |                |         |              |
| <b>Heat deflection temperature</b>                |                |         |              |
| at 1.80 MPa (HDT/A)                               | 45             | °C      | ISO 75-2     |
| at 0.45 MPa (HDT/B)                               | 72             | °C      | ISO 75-2     |
| <b>Vicat Softening Temperature</b> <sup>(5)</sup> |                |         |              |
| at 50 N (VST/B)                                   | 72             | °C      | ISO 306      |
| <b>DSC test</b>                                   |                |         |              |
| melting point                                     | 124 – 128      | °C      | DIN 53765    |

© 2026 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



- (1) Speed of testing: 50 mm/min
- (2) Test specimen according to ISO 527-2 type 1BA, thickness 2 mm
- (3) Determined in 2% Arkopal N100 at 80 °C, 4 MPa
- (4) Publication in Science Direct, Polymer no. 46 (2005) 6369-6379
- (5) Conditioning of test specimen: temp. 23 °C, relative humidity 50 %, 24 hours

### STORAGE AND HANDLING

Polyethylenes resins (in pelletised or powder form) should be stored in such a way that it prevents exposure to direct sunlight and/or heat, as this may lead to quality deterioration. The storage location should also be dry, dust free and the ambient temperature should not exceed 50 °C. Not complying with these precautionary measures can lead to a degradation of the product which can result in colour changes, bad smell and inadequate product performance. It is also advisable to process polyethylene resins (in pelletised or powder form) within 6 months after delivery, this because also excessive aging of polyethylene can lead to a deterioration in quality.

### ENVIRONMENT AND RECYCLING

The environmental aspects of any packaging material do not only imply waste issues but have to be considered in relation with the use of natural resources, the preservations of foodstuffs, etc. SABIC considers polyethylene to be an environmentally efficient packaging material. Its low specific energy consumption and insignificant emissions to air and water designate polyethylene as the ecological alternative in comparison with the traditional packaging materials. Recycling of packaging materials is supported by SABIC whenever ecological and social benefits are achieved and where a social infrastructure for selective collecting and sorting of packaging is fostered. Whenever 'thermal' recycling of packaging (i.e. incineration with energy recovery) is carried out, polyethylene -with its fairly simple molecular structure and low amount of additives- is considered to be a trouble-free fuel.

### DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

