

For more information and technical assistance contact:

Chevron Phillips Chemical
P.O. Box 4910
The Woodlands, TX 77387-4910
800.231.1212



SUPERIOR FLEXIBLE PACKAGING RESINS

Marlex® 5619 Polyethylene

LOW DENSITY POLYETHYLENE (LDPE)

This low density polyethylene is tailored for blown film applications that require:

- Superior strength
- Good abrasion and tear resistance
- Exceptional shrink and shrink tension
- Low coefficient of friction

Typical blown film applications include:

- Heavy duty packaging
- Pallet shrink
- Case shrink wrap
- C&A film and container liners

Nominal Resin Properties	English	SI	Method
Melt Index, 190 °C/2.16 kg	---	0.4 g/10 min	ASTM D1238
Density	---	0.922 g/cm ³	ASTM D1505
Slip	400 ppm	400 ppm	---
Antiblock	1500 ppm	1500 ppm	---
Vicat Softening Temperature	219 °F	104 °C	ASTM D1525
Melting Point	231 °F	110 °C	ASTM D3418

Nominal Blown Film Properties at 2.0 mil ^{1,2}	English	SI	Method
Haze	8 %	8 %	ASTM D1003
Gloss, 60°	100	100	ASTM D2457
COF	0.13	0.13	ASTM D1894
Dart	---	225 g	ASTM D1709
Elmendorf Tear MD/TD	---	245/215 g	ASTM D1922
Tensile Strength at Break MD/TD	4000/3900 psi	27/27 MPa	ASTM D882
Tensile Elongation at Break MD/TD	220/570 %	220/570 %	ASTM D882
1 % Secant Modulus MD/TD	29500/34500 psi	203/238 MPa	ASTM D882
WVTR	0.65 g/100in ² /day	10 g/m ² /day	ASTM F1249
OTR	250 cm ³ /100in ² /day	3500 cm ³ /m ² /day	ASTM D3985

1. Produced on a LDPE line at 2.5:1 BUR, 35 mil die gap, 8 in. die, 250 lb/h, 400 °F melt temperature.
2. Not recommended for gauges under 2.0 mil

