

VALOX™ RESIN EH7020

REGION AMERICAS

DESCRIPTION

MINERAL FILLED, METALLIZABLE

TYPICAL PROPERTY VALUES

Revision 20260509

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	57	MPa	ASTM D638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	103	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	4130	MPa	ASTM D790
IMPACT			
Izod Impact, unnotched, 23°C	389	J/m	ASTM D4812
Izod Impact, notched, 23°C	32	J/m	ASTM D256
THERMAL			
HDT, 0.45 MPa, 6.4 mm, unannealed	187	°C	ASTM D648
HDT, 1.82 MPa, 6.4 mm, unannealed	105	°C	ASTM D648
CTE, -40°C to 40°C, flow	5.58E-05	1/°C	ASTM E831
PHYSICAL			
Specific Gravity	1.49	-	ASTM D792
Mold Shrinkage, flow, 1.5-3.2 mm	1.4 – 1.6	%	SABIC method
Mold Shrinkage, flow, 3.2-4.6 mm	1.5 – 1.6	%	SABIC method
Mold Shrinkage, xflow, 1.5-3.2 mm	1.3 – 1.4	%	SABIC method
Mold Shrinkage, xflow, 3.2-4.6 mm	1.4 – 1.5	%	SABIC method
Melt Volume Rate, MVR at 265°C/2.16 kg	40	cm³/10 min	ISO 1133
ELECTRICAL			
Dielectric Strength, in oil, 3.2 mm	16.9	kV/mm	ASTM D149
Relative Permittivity, 50/60 Hz	3.1	-	ASTM D150
Relative Permittivity, 1 MHz	2.9	-	ASTM D150
Dissipation Factor, 50/60 Hz	0.0039	-	ASTM D150
Dissipation Factor, 1 MHz	0.014	-	ASTM D150
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	3 – 4	Hrs	
Drying Time (Cumulative)	12	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	250 – 265	°C	
Nozzle Temperature	245 – 260	°C	
Front - Zone 3 Temperature	250 – 265	°C	
Middle - Zone 2 Temperature	245 – 260	°C	
Rear - Zone 1 Temperature	240 – 255	°C	
Mold Temperature	65 – 90	°C	
Back Pressure	0.3 – 0.7	MPa	

© 2026 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Screw Speed	50 – 80	rpm	
Shot to Cylinder Size	40 – 80	%	
Vent Depth	0.025 – 0.038	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

PETROMALL

