

VALOX™ RESIN HX312C

REGION EUROPE

DESCRIPTION

Unreinforced PBT with release. For medical devices and pharmaceutical applications. Healthcare management of change, biocompatible (ISO 10993 or USP Class VI), food contact compliant. EtO and steam sterilizable.

TYPICAL PROPERTY VALUES

Revision 20180807

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	51	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	30	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	6	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	25	%	ASTM D638
Tensile Modulus, 50 mm/min	2500	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	82	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2340	MPa	ASTM D790
Tensile Stress, yield, 50 mm/min	58	MPa	ISO 527
Tensile Stress, break, 50 mm/min	30	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	6	%	ISO 527
Tensile Strain, break, 50 mm/min	25	%	ISO 527
Tensile Modulus, 1 mm/min	2500	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	85	MPa	ISO 178
Flexural Modulus, 2 mm/min	2400	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	53	J/m	ASTM D256
Izod Impact, notched, -30°C	53	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	40	J	ASTM D3763
Izod Impact, unnotched 80°10'4 +23°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80°10'4 -30°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, notched 80°10'4 +23°C	3	kJ/m ²	ISO 180/1A
Izod Impact, notched 80°10'4 -30°C	3	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80°10'4 sp=62mm	3	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80°10'4 sp=62mm	2	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80°10'4 sp=62mm	NB	kJ/m ²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80°10'4 sp=62mm	NB	kJ/m ²	ISO 179/1eU
THERMAL			
Vicat Softening Temp, Rate B/50	175	°C	ASTM D1525
HDT, 1.82 MPa, 3.2mm, unannealed	54	°C	ASTM D648
CTE, -40°C to 40°C, flow	1.E-04	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	1.E-04	1/°C	ASTM E831
CTE, 23°C to 80°C, flow	1.E-04	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	1.E-04	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	175	°C	ISO 306

© 2024 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Vicat Softening Temp, Rate B/120	165	°C	ISO 306
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	58	°C	ISO 75/Ae
PHYSICAL			
Specific Gravity	1.31	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm	0.9 – 1.6	%	SABIC method
Melt Flow Rate, 250°C/1.2 kgf	35	g/10 min	ASTM D1238
Density	1.31	g/cm³	ISO 1183
Water Absorption, (23°C/saturated)	0.35	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.08	%	ISO 62
Melt Volume Rate, MVR at 250°C/1.2 kg	31	cm³/10 min	ISO 1133
INJECTION MOLDING			
Drying Temperature	110 – 120	°C	
Drying Time	2 – 4	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	250 – 270	°C	
Nozzle Temperature	240 – 260	°C	
Front - Zone 3 Temperature	245 – 265	°C	
Middle - Zone 2 Temperature	240 – 255	°C	
Rear - Zone 1 Temperature	230 – 245	°C	
Hopper Temperature	40 – 60	°C	
Mold Temperature	40 – 100	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

