

VALOX™ RESIN K3501

REGION AMERICAS

DESCRIPTION

Unfilled PBT, Hydrollytically Stable, Heat Stabilized, Impact Modified. A hydrollytically stable grade designed for improved performance under heat/humidity environments. Targeted at automotive underhood applications requiring USCAR-2 Class III humidity/heat performance.

TYPICAL PROPERTY VALUES

Revision 20190815

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	50	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	25	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	3.5	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	51	%	ASTM D638
Tensile Modulus, 50 mm/min	2400	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	70	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2100	MPa	ASTM D790
Tensile Stress, yield, 50 mm/min	50	MPa	ISO 527
Tensile Stress, break, 50 mm/min	73	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	3.3	%	ISO 527
Tensile Strain, break, 50 mm/min	37	%	ISO 527
Tensile Modulus, 1 mm/min	2100	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	73	MPa	ISO 178
Flexural Modulus, 2 mm/min	2000	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, -30°C	NB	J/m	ASTM D4812
Izod Impact, notched, 23°C	90	J/m	ASTM D256
Izod Impact, notched, 0°C	83	J/m	ASTM D256
Izod Impact, notched, -20°C	75	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	48	J	ASTM D3763
Instrumented Impact Total Energy, -40°C	60	J	ASTM D3763
Izod Impact, unnotched 80°10°4 -30°C	NB	kJ/m²	ISO 180/1U
Izod Impact, notched 80°10°4 +23°C	8	kJ/m²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80°10°4 sp=62mm	10	kJ/m²	ISO 179/1eA
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	127	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	46	°C	ASTM D648
CTE, -40°C to 40°C, flow	9.1E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	9.7E-05	1/°C	ISO 11359-2
Ball Pressure Test, 75°C +/- 2°C	NA	-	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	170	°C	ISO 306
Vicat Softening Temp, Rate B/120	170	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80°10°4 sp=64mm	46	°C	ISO 75/Af
PHYSICAL			

© 2024 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Mold Shrinkage, flow, 3.2 mm	1.7 – 2.6	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	1.7 – 2.6	%	SABIC method
Density	1.28	g/cm ³	ISO 1183
Water Absorption, (23°C/saturated)	0.34	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.08	%	ISO 62
Melt Volume Rate, MVR at 250°C/2.16 kg	26	cm ³ /10 min	ISO 1133
FLAME CHARACTERISTICS			
UL Yellow Card Link	E121562-100657103	-	-
AFTER 40 CYCLES, SIMILAR TO USCAR-2, CLASS III			
Tensile Stress, brk, Type I, 50 mm/min	37	MPa	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	12	%	ASTM D638
Flexural Modulus, 1.3 mm/min, 50 mm span	2350	MPa	ASTM D790
Instrumented Impact, Total Energy, 23°C	58	J	ASTM D3763
PROPERTIES AFTER 1008 HOURS AT 125°C			
Tensile Stress, yld, Type I, 50 mm/min	54	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	4	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	25	%	ASTM D638
Flexural Modulus, 1.3 mm/min, 50 mm span	2330	MPa	ASTM D790
Instrumented Impact, Total Energy, 23°C	61	J	ASTM D3763
INJECTION MOLDING			
Drying Temperature	60 – 75	°C	
Drying Time	4 – 5	Hrs	
Drying Time (Cumulative)	8	Hrs	
Maximum Moisture Content	0.05	%	
Melt Temperature	250 – 265	°C	
Nozzle Temperature	245 – 260	°C	
Front - Zone 3 Temperature	250 – 265	°C	
Middle - Zone 2 Temperature	245 – 260	°C	
Rear - Zone 1 Temperature	240 – 255	°C	
Mold Temperature	65 – 90	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	50 – 80	rpm	
Shot to Cylinder Size	40 – 80	%	
Vent Depth	0.025 – 0.038	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

