

VALOX™ RESIN K3501

REGION EUROPE

DESCRIPTION

Unfilled PBT, Hydrolytically Stable, Heat Stabilized, Impact Modified. A hydrolytically stable grade designed for improved performance under heat/humidity environments. Targeted at automotive underhood applications requiring USCAR-2 Class III humidity/heat performance.

TYPICAL PROPERTY VALUES

Revision 20190815

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	50	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	25	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	3.3	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	50	%	ASTM D638
Tensile Modulus, 50 mm/min	2400	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	70	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2100	MPa	ASTM D790
Tensile Stress, yield, 50 mm/min	50	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	3.5	%	ISO 527
Tensile Strain, break, 50 mm/min	40	%	ISO 527
Tensile Modulus, 1 mm/min	2100	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	73	MPa	ISO 178
Flexural Modulus, 2 mm/min	2000	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, -30°C	NB	J/m	ASTM D4812
Izod Impact, notched, 23°C	90	J/m	ASTM D256
Izod Impact, notched, 0°C	83	J/m	ASTM D256
Izod Impact, notched, -20°C	75	J/m	ASTM D256
Izod Impact, unnotched 80°10'4 -30°C	NB	kJ/m²	ISO 180/1U
Izod Impact, notched 80°10'4 +23°C	8	kJ/m²	ISO 180/1A
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	46	°C	ASTM D648
CTE, -40°C to 40°C, flow	9.1E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	9.7E-05	1/°C	ISO 11359-2
Ball Pressure Test, 75°C +/- 2°C	NA	-	IEC 60695-10-2
Vicat Softening Temp, Rate B/120	165	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80°10'4 sp=64mm	46	°C	ISO 75/Af
PHYSICAL			
Density	1.28	g/cm³	ISO 1183
Water Absorption, (23°C/saturated)	0.34	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.08	%	ISO 62
Melt Volume Rate, MVR at 250°C/2.16 kg	26	cm³/10 min	ISO 1133
FLAME CHARACTERISTICS			
UL Yellow Card Link	E45329-101938116	-	-

© 2024 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
INJECTION MOLDING			
Drying Temperature	60 – 75	°C	
Drying Time	4 – 5	Hrs	
Drying Time (Cumulative)	8	Hrs	
Maximum Moisture Content	0.05	%	
Melt Temperature	250 – 265	°C	
Nozzle Temperature	245 – 260	°C	
Front - Zone 3 Temperature	250 – 265	°C	
Middle - Zone 2 Temperature	245 – 260	°C	
Rear - Zone 1 Temperature	240 – 255	°C	
Mold Temperature	65 – 90	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	50 – 80	rpm	
Shot to Cylinder Size	40 – 80	%	
Vent Depth	0.025 – 0.038	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

