

VALOX™ RESIN PDR4922

REGION ASIA

DESCRIPTION

GF filled PBT grade

TYPICAL PROPERTY VALUES

Revision 20180807

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	85	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	81	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	2.4	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	3.3	%	ASTM D638
Tensile Modulus, 50 mm/min	5410	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	133	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	4580	MPa	ASTM D790
Tensile Stress, yield, 50 mm/min	85	MPa	ISO 527
Tensile Stress, break, 50 mm/min	81	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	3	%	ISO 527
Tensile Strain, break, 50 mm/min	3.6	%	ISO 527
Tensile Modulus, 1 mm/min	5230	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	130	MPa	ISO 178
Flexural Modulus, 2 mm/min	4860	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	102	J/m	ASTM D256
Izod Impact, notched, -30°C	58	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	8	J	ASTM D3763
Izod Impact, notched 80°10°4 +23°C	10	kJ/m²	ISO 180/1A
Izod Impact, notched 80°10°4 -30°C	6	kJ/m²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80°10°4 sp=62mm	8	kJ/m²	ISO 179/1eA
THERMAL			
Vicat Softening Temp, Rate B/50	200	°C	ASTM D1525
HDT, 0.45 MPa, 3.2 mm, unannealed	216	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	184	°C	ASTM D648
CTE, -40°C to 40°C, flow	4.18E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	1.14E-04	1/°C	ASTM E831
CTE, -40°C to 40°C, flow	4.39E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	1.18E-04	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	195	°C	ISO 306
Vicat Softening Temp, Rate B/120	196	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80°10°4 sp=64mm	170	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.4	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm	0.16	%	SABIC method

© 2024 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Mold Shrinkage, xflow, 3.2 mm	0.94	%	SABIC method
Melt Flow Rate, 250°C/2.16 kgf	13.4	g/10 min	ASTM D1238
Density	1.4	g/cm³	ISO 1183
Water Absorption, (23°C/saturated)	0.03	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.03	%	ISO 62
Melt Volume Rate, MVR at 250°C/2.16 kg	12	cm³/10 min	ISO 1133
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	3 – 4	Hrs	
Drying Time (Cumulative)	12	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	250 – 265	°C	
Nozzle Temperature	245 – 260	°C	
Front - Zone 3 Temperature	250 – 265	°C	
Middle - Zone 2 Temperature	245 – 260	°C	
Rear - Zone 1 Temperature	240 – 255	°C	
Mold Temperature	50 – 75	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	50 – 100	rpm	
Shot to Cylinder Size	40 – 80	%	
Vent Depth	0.025 – 0.038	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

