

VALOX™ RESIN SHF436HR

REGION AMERICAS

DESCRIPTION

PBT, Super High Flow, 30% glass reinforced, hydrolytically resistant.

TYPICAL PROPERTY VALUES

Revision 20180920

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	111	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	111	MPa	ASTM D638
Tensile Strain, yld, Type I, 5 mm/min	2	%	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	2	%	ASTM D638
Tensile Modulus, 5 mm/min	11900	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	163	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	8700	MPa	ASTM D790
Tensile Stress, yield, 5 mm/min	117	MPa	ISO 527
Tensile Stress, break, 5 mm/min	117	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	2	%	ISO 527
Tensile Strain, break, 5 mm/min	2	%	ISO 527
Tensile Modulus, 1 mm/min	9490	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	165	MPa	ISO 178
Flexural Modulus, 2 mm/min	7720	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	92	J/m	ASTM D256
Izod Impact, notched, -30°C	95	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	6	J	ASTM D3763
Izod Impact, notched 80°10'4 +23°C	8	kJ/m²	ISO 180/1A
Izod Impact, notched 80°10'4 -30°C	8	kJ/m²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80°10'4 sp=62mm	8	kJ/m²	ISO 179/1eA
THERMAL			
Vicat Softening Temp, Rate B/50	200	°C	ASTM D1525
HDT, 1.82 MPa, 3.2mm, unannealed	214	°C	ASTM D648
CTE, -40°C to 40°C, flow	1.E-04	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	3.E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, flow	1.E-04	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	3.E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	200	°C	ISO 306
Vicat Softening Temp, Rate B/120	200	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80°10'4 sp=64mm	206	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.53	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm	0.3 – 0.5	%	SABIC method
Melt Flow Rate, 250°C/2.16 kgf	30	g/10 min	ASTM D1238

© 2024 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Density	1.53	g/cm ³	ISO 1183
Water Absorption, (23°C/saturated)	0.28	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.06	%	ISO 62
Melt Volume Rate, MVR at 250°C/2.16 kg	30	cm ³ /10 min	ISO 1133
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	3 – 4	Hrs	
Drying Time (Cumulative)	12	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	250 – 265	°C	
Nozzle Temperature	245 – 260	°C	
Front - Zone 3 Temperature	250 – 265	°C	
Middle - Zone 2 Temperature	245 – 260	°C	
Rear - Zone 1 Temperature	240 – 255	°C	
Mold Temperature	65 – 90	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	50 – 80	rpm	
Shot to Cylinder Size	40 – 80	%	
Vent Depth	0.025 – 0.038	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

